

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C08F 2/00, C09J 123/16	A1	(11) International Publication Number: WO 97/33921 (43) International Publication Date: 18 September 1997 (18.09.97)													
<p>(21) International Application Number: PCT/US97/04161</p> <p>(22) International Filing Date: 14 March 1997 (14.03.97)</p> <p>(30) Priority Data:</p> <table border="0"> <tr> <td>08/615,750</td> <td>14 March 1996 (14.03.96)</td> <td>US</td> </tr> <tr> <td>08/616,406</td> <td>15 March 1996 (15.03.96)</td> <td>US</td> </tr> </table> <p>(60) Parent Applications or Grants</p> <p>(63) Related by Continuation</p> <table border="0"> <tr> <td>US</td> <td>08/615,750 (CIP)</td> </tr> <tr> <td>Filed on</td> <td>14 March 1996 (14.03.96)</td> </tr> <tr> <td>US</td> <td>08/616,406 (CIP)</td> </tr> <tr> <td>Filed on</td> <td>15 March 1996 (15.03.96)</td> </tr> </table> <p>(71) Applicants (for all designated States except US): THE DOW CHEMICAL COMPANY [US/US]; 2030 Dow Center, Midland, MI 48674 (US). H.B. FULLER LICENSING & FINANCING INC. [US/US]; 1200 Wolters Boulevard, Saint Paul, MN 55110 (US).</p> <p>(72) Inventors; and</p> <p>(75) Inventors/Applicants (for US only): SIMMONS, Eugene, R. [US/US]; 3440 Montmorency Street, Vadnais Heights, MN 55110 (US). BUNNELLE, William, L. [US/US];</p>	08/615,750	14 March 1996 (14.03.96)	US	08/616,406	15 March 1996 (15.03.96)	US	US	08/615,750 (CIP)	Filed on	14 March 1996 (14.03.96)	US	08/616,406 (CIP)	Filed on	15 March 1996 (15.03.96)	<p>16137 Lexington Avenue N.E., Circle Pines, MN 55304 (US). MALCOLM, David, B. [US/US]; 2190 German Street, Maplewood, MN 55109 (US). KNUTSON, Keith, C. [US/US]; Apartment Number 3214, 138 Lexington Avenue, Shoreview, MN 55126 (US). KAUFFMAN, Thomas, F. [US/US]; 7144 Sherwood Road, Woodbury, MN 55125 (US). KROLL, Mark, S. [US/US]; 3324 Katie Lane, Arden Hills, MN 55112 (US). KEEHR, Michael, S. [US/US]; 4128 5th Avenue South, Minneapolis, MN 55407 (US). PARIKH, Deepak, R. [US/US]; 59 North Trillium Court, Lake Jackson, TX 77566 (US). ALLEN, Jimmy, D. [US/US]; Route 4, 200 Marion, Brazoria, TX 77422 (US). SPETH, David, R. [US/US]; 1207 Evamar Drive, Midland, MI 48640 (US). YALVAC, Selim [US/US]; 210 Teakwood Street, Lake Jackson, TX 77566 (US). FINLAYSON, Malcolm, F. [US/US]; 731 East 12 1/2 Street, Houston, TX 77008 (US). RICKEY, Cyndi, L. [US/US]; 315 Carnation, Lake Jackson, TX 77566 (US).</p> <p>(74) Agent: WARRICK, Noreen, D.; The Dow Chemical Company, Patent Dept., B-1211, 2301 Brazosport Boulevard, Freeport, TX 77541 (US).</p> <p>(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ARIPO patent (GH, KE, LS, MW, SD, SZ, UG), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).</p> <p>Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i></p>
08/615,750	14 March 1996 (14.03.96)	US													
08/616,406	15 March 1996 (15.03.96)	US													
US	08/615,750 (CIP)														
Filed on	14 March 1996 (14.03.96)														
US	08/616,406 (CIP)														
Filed on	15 March 1996 (15.03.96)														
<p>(54) Title: ADHESIVES COMPRISING OLEFIN POLYMERS</p> <p>(57) Abstract</p> <p>Disclosed are adhesives and processes for preparing the same, comprising at least one first homogeneous ethylene/α-olefin interpolymer, and optionally at least one tackifier, and optionally at least one plasticizer. The claimed adhesives are useful as adhesives such as are employed in various applications, such as in masking tape, clear office tape, labels, decals, bandages, decorative and protective sheets (such as shelf and drawer liners), floor tiles, sanitary napkin/incontinence device placement strips, sun control films, the joining of gaskets to automobile windows, packaging, bookbinding, construction of nonwoven articles, and insulation bonding.</p>															

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgystan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

ADHESIVES COMPRISING OLEFIN POLYMERS

The subject invention relates to hot melt adhesives comprising at least one homogeneous linear or substantially linear interpolmer of ethylene with at least one
5 C₃-C₂₀ α -olefin, further characterized by each said interpolmer having a polydispersity less than about 2.5, and articles constructed therefrom. Such hot melt adhesives are useful in a variety of applications including but not limited to bookbinding, case and carton seal, packaging, glue sticks, foam in place gaskets, and particularly pressure sensitive adhesives for tag and label adhesives, palletizing
10 adhesives, skin attachment adhesives, positioning adhesives, diaper tapes and construction adhesives for assembly of nonwoven articles, etc.

Historically, adhesives have been based on any of five polymer classes: polyethylene; ethylene vinyl acetate; natural rubber or block copolymer elastomers (for example, styrene-isoprene-styrene block copolymers, styrene-butadiene-styrene
15 block copolymers, and styrene-butadiene random copolymers); acrylics (such as interpolymers of butyl acrylate, 2-ethyl hexyl acrylate, and methyl methacrylate); and amorphous polyolefins, and the like, amorphous C₃ and greater α -olefins, such as atactic polypropylene, copolymers of propylene and higher order α -olefins, and polybutene.

20 Linear low density polyethylene and low density polyethylene have been used as a base polymer in a variety of hot melt adhesives, particularly for case and carton sealing, wherein upon cooling and solidifying the resulting adhesive is relatively tack free. Polyethylene waxes are also used in formulating hot melt adhesives. Linear low density polyethylene and low density polyethylene, as base raw materials for
25 adhesives, suffer from the disadvantage that due to their crystalline nature, they tend to be very stiff and have poor cold temperature properties. In addition to poor cold temperature properties, polyethylene case and carton seal adhesives have limited hot tack, resulting in low peel adhesion failure temperatures. Further, polyethylene has had limited utility as a base polymer in formulating pressure sensitive adhesives,
30 particularly due to poor oil holding capability.

Ethylene vinyl acetate (EVA) based systems are limited in that as higher vinyl acetate levels are selected, although crystallinity decreases and elastomeric performance increase, compatibility with formulation ingredients decreases.

Accordingly, EVA is typically utilized in non-pressure sensitive adhesive applications.

5 Block copolymer elastomers provide an excellent balance of tack, peel resistance and creep resistance properties. Such elastomers may be utilized in solvent-based, water-born, and hot melt pressure sensitive adhesives. However, adhesive systems based on such elastomers are disadvantageous in that the sites of unsaturation in the block copolymer backbone make the adhesive susceptible to degradation by the
10 action of oxygen and ultraviolet light.

Acrylic systems, while stable to oxygen and ultraviolet light, are inferior to block copolymer elastomer systems in terms of the balance of tack, peel and creep resistance. Further, such systems are typically available only in the solvent-based and water-borne systems, making them further disadvantageous for the reasons set forth
15 above.

Amorphous polyolefins have been utilized in adhesive systems, at least in part to provide improved stability to oxygen and ultraviolet light, as compared to block copolymer elastomer systems. Due to the fact that amorphous polyolefins have been historically available as reaction by-products, they have been inconsistent in grade,
20 composition, and viscosity, leading to a poor balance of properties. In particular, poly-1-butene has a tendency to slowly crystallize after application to the substrate, leading to a profound loss of tack. When oil is added to increase tack, the oil tends to migrate out of the adhesive into the backing layer or the substrate. Due to the heterogeneity of branch distribution and broad molecular weight distribution, adhesives comprising less
25 than 40 weight percent amorphous polyolefins tend to be weak cohesively, suffer from low tensile strength, and leave a residue on the substrate surface after peeling. To compensate for their inherent poor cohesive strength, adhesives based on amorphous polyolefins tend to have a high concentration of amorphous polyolefin, resulting in a relatively high viscosity. Such high viscosity renders amorphous
30 polyolefin-based adhesives unsuitable for use with spray application equipment at typical application temperatures of less than about 325°F (167°C). Amorphous

polyolefins further disadvantageously tend to have unpredictable aging characteristics due to an uncontrolled secondary crystallization caused by the random chain length and distribution of the comonomer branching.

Homogeneous linear and substantially linear ethylene polymers prepared using
5 single-site or metallocene catalysts have been recently introduced. Homogeneous ethylene polymers are characterized as having a narrow molecular weight distribution and a uniform short-chain branching distribution. In the case of substantially linear ethylene polymers, such homogeneous ethylene polymers are further characterized as having long chain branching. Substantially linear ethylene polymers are commercially
10 available from The Dow Chemical Company as Affinity™ polyolefin plastomers, which are produced using Dow's Insite™ technology. Homogeneous linear ethylene polymers are available from Exxon Chemical Company under the trade name Exact® plastomers.

Tse et al., U.S. Patent No. 5,530,054, claims a hot melt adhesive composition
15 consisting essentially of: (a) 30 - 70 weight percent of a copolymer of ethylene and about 6 to about 30 weight percent of a C₄ to C₂₀ α-olefin produced in the presence of a catalyst composition comprising a metallocene and an alumoxane and having an M_w of from about 20,000 to about 100,000; and (b) a hydrocarbon tackifier which is selected from a recited list. Exemplified are compositions consisting of 45 weight
20 percent of ethylene/butene-1 copolymer having a specific gravity of either 0.898 g/cm³ or 0.901 g/cm³.

Tse et al, U.S. Patent No. 5,548,014, claims a hot melt adhesive composition comprising a blend of ethylene/α-olefin copolymers wherein the first copolymer has a M_w from about 20,000 to about 39,000 and the second copolymer has a M_w from about
25 40,000 to about 100,000. Each of the hot melt adhesives exemplified comprises a blend of copolymers, contains 45 weight percent copolymer, with at least one of the copolymers having a polydispersity greater than 2.5. Furthermore, the lowest density copolymer exemplified has a specific gravity of 0.894 g/cm³.

However, Tse, in Application of Adhesion Model for Developing Hot Melt
30 Adhesives Bonded to Polyolefin Surfaces, Journal of Adhesion, Vol. 48, Issue 1-4, pp. 149 to 167 (1995), notes that compared with hot melt adhesives based on

ethylene/vinyl acetate copolymer, hot melt adhesives based on homogeneous linear ethylene/ α -olefin interpolymers show higher viscosity and inferior tensile strength, but better bond strength to polyolefin surfaces, higher strain at break and lower yield stress.

5 Lakshmanan et al., U.S. Pat. No. 5,397,843, teaches blended polymer compositions comprising an admixture of a copolymer of ethylene and an α -olefin and an amorphous polypropylene and/or amorphous polyolefin, or mixtures thereof. A hot melt adhesive is claimed comprising from 20 to 97.5 percent of a traditional polyolefin. The examples set forth in Lakshmanan teach compositions with high
10 concentrations, at least 42.5 percent by weight, of blended polymers and tend to suffer from the previously described disadvantages of traditional polyolefins. The single ethylene and α -olefin exemplified is "Flexomer 9042" from Union Carbide, having a 1-butene content of 15 weight percent, a melt index of 5.0 g/10 minute, a crystallinity level of 26 percent and a density of 0.900 g/cm³. The "Flexomer" polyolefin from
15 Union Carbide depicted in the examples is believed to have a polydispersity greater than 2.5.

Those in industry would find great advantage in hot melt adhesives based on homogeneous ethylene/ α -olefin interpolymers which have a balance of properties which is superior to those which have been previously attained.

20 Accordingly, the subject invention pertains to an adhesive comprising:

- (a) from 5 to 95 weight percent of at least one interpolymer which is a homogeneous linear or substantially linear ethylene/ α -olefin interpolymer characterized as having a density from 0.850 to 0.885 g/cm³;
- 25 (b) from 0 to 95 weight percent of at least one tackifier;
- (c) from 0 to about 90 weight percent of at least one plasticizer; and
- (d) from 0 to 90 weight percent of at least one wax;

wherein the sum of components (b), (c), and (d) comprises 5 to 95 weight percent of said adhesive composition.

30 The subject invention further pertains to a hot melt adhesive composition comprising:

- 5
- (a) a homogeneous linear interpolmer of ethylene and greater than 30 weight percent as determined by mass balance, based on the total weight of ethylene and comonomer, of an α -olefin comonomer having from 3 to 20 carbon atoms, which copolymer has a weight average molecular weight (M_w) of from 2000 to 100,000; and
 - (b) a tackifier.

The subject invention further pertains to an adhesive comprising:

- 10
- (a) from 5 to 95 weight percent of at least one interpolmer which is a homogeneous linear or substantially linear ethylene/ α -olefin interpolmer characterized as having a weight average molecular weight (M_w) of less than 20,000;
 - (b) from 0 to 95 weight percent of at least one tackifier;
 - (c) from 0 to about 90 weight percent of at least one plasticizer; and
 - 15 (d) from 0 to 90 weight percent of at least one wax;

wherein the sum of components (b), (c), and (d) comprises 5 to 95 weight percent of said adhesive composition.

The subject invention further provides various adhesive compositions which are targeted for use in various adhesive applications. In this regard, the
20 subject invention further pertains to a hot melt adhesive comprising:

- (a) from 30 to 97 weight percent of at least one first polymer which is an interpolmer of ethylene and at one C_3 - C_{20} α -olefin, said at least one first polymer being characterized as having:
 - 25 (i) a density of from 0.850 to 0.885 g/cm³,
 - (iii) a number average molecular weight as determined by gel permeation chromatography, of less than 20,000;
- (b) from 3 to 70 weight percent of at least one second
30 polymer which is an ethylene homopolymer or an interpolmer of ethylene with at least C_3 - C_{20} α -olefin,

the at least one second polymer being characterized as having:

- (i) a density of from 0.910 to 0.970 g/cm³,
- (ii) a number average molecular weight as determined by gel permeation chromatography, of less than 6,000; and

5

- (c) from 0 to 70 weight percent of one or more tackifiers.

In one preferred embodiment, the adhesive compositions of the present invention are pressure sensitive adhesives, which are characterized as having a storage modulus (G') at 25°C of less than 1×10^7 dynes/cm² (1 MPa) and a glass transition temperature (T_g) of from -65°C to 30°C, more preferably from 0°C to 20°C and most preferably from 10°C to 20°C.

Optionally, the adhesive composition of the invention may further contain an additional polymer selected from the group consisting of compatible elastomers, such as a thermoplastic block copolymer, polyamides, amorphous or crystalline polyolefins such as polypropylene, polybutylene or polyethylene, wherein M_w is greater than about 3000; interpolymers or ionomers of ethylene with at least one comonomer selected from the group consisting of vinyl esters of a saturated carboxylic acid having up to 4 carbon atoms, unsaturated mono- or dicarboxylic acids of 3 to 5 carbon atoms, or salts or esters thereof; and mixtures thereof.

In one embodiment, the invention provides hot melt adhesives comprising homogeneous ethylene polymers in conjunction with low density polyethylene or heterogeneously branched linear low density polyethylene having a weight average molecular weight (M_w) greater than about 3000, ethylene-vinyl acetate (EVA), or a polyamide.

Optionally, the at least one ethylene/ α -olefin interpolymer utilized in the hot melt adhesives of the invention may be provided in conjunction with a second homogeneous linear or substantially linear interpolymer, which differs in at least one physical property selected from the group consisting of density, comonomer type, number average molecular weight and combinations thereof. The interpolymers may be blended at ratios ranging from 0.05 to 20 ratio by weight to 20 to 0.05 ratio by weight.

30

In a preferred embodiment, a first homogeneous ethylene/ α -olefin interpolymer having a density less than 0.870 g/cm^3 is provided in conjunction with a second homogeneous ethylene/ α -olefin interpolymer having a density greater than 0.900 g/cm^3 .

5 In one particularly preferred embodiment, the subject invention provides a hot melt adhesive comprising :

(a) from 5 - 95 weight percent of a polymer mixture which in turn comprises:

10 (i) from 30 to 97 weight percent of at least one first polymer which is an interpolymer of ethylene and at least one $\text{C}_3\text{-C}_{20}$ α -olefin, the at least one first polymer being characterized as having a density of from 0.850 to 0.920 g/cm^3 , and a number average molecular weight as determined by gel permeation chromatography, of less than 80,000; and

15 (ii) from 3 to 70 weight percent of at least one second polymer which is an ethylene homopolymer or an interpolymer of ethylene and at least one $\text{C}_3\text{-C}_{20}$ α -olefin, the at least one second polymer being characterized as having a density of from 0.910 to 0.970 g/cm^3 and a number average molecular weight as determined by gel permeation chromatography, of less than 6,000; and

20 (b) from 0 to 95 weight percent of at least one tackifier;

(c) from 0 to about 90 weight percent of at least one plasticizer; and

25 (d) from 0 to 90 weight percent of at least one wax;.

30 wherein the density of the at least one first polymer and the at least one second polymer differ by at least 0.01 g/cm^3 and the number average molecular weights of the at least one first polymer and the at least one second polymer differ by at least 5000.

The subject invention further provides a polymerization process comprising:

- 5
- (a) reacting by contacting ethylene and at least one C₃-C₂₀ α-olefin, under solution polymerization conditions, in the presence of a single site catalyst composition, in at least one reactor, to produce a solution of a first polymer which is an interpolymer of ethylene and the at least one C₃-C₂₀ α-olefin, the at least one first polymer being characterized as having:
- 10
- (i) a density of from 0.850 to 0.920 g/cm³,
 - (ii) a number average molecular weight as determined by gel permeation chromatography, of from 5,000 to 80,000; and
 - (iii) a molecular weight distribution (M_w/M_n) of from 1.5 to 2.5;
- 15
- (b) reacting by contacting ethylene and, optionally, at least one C₃-C₂₀ α-olefin, under solution polymerization conditions, in the presence of a single site catalyst composition or a heterogeneous catalyst composition, in at least one other reactor, to produce a solution of at least one second polymer, which is an ethylene homopolymer or an interpolymer of ethylene with the at least one C₃-C₂₀ α-olefin, the at least one second polymer being characterized as having:
- 20
- (i) a density of from 0.910 to 0.970 g/cm³,
 - (ii) a number average molecular weight as determined by gel permeation chromatography, of less than 6,000, and
 - (iii) a molecular weight distribution (M_w/M_n) of from 1.5 to 2.5;
- 25
- 30
- (c) combining the solution of the first reactor with the solution of the second reactor to form a solution of a blend;

- (d) removing the solvent from the solution of a blend of step (c) and recovering the blend; and
- (e) optionally introducing a tackifier into the reactor of step (a), the reactor of step (b), or at any point subsequent to the reacting of step (b).

5
10
15
In general, the adhesive composition of the present invention exhibits improved properties, including excellent viscosity and color stability, particularly at elevated temperatures; high cohesive strength and excellent oil holding power, allowing the use of relatively low concentrations of the employed homogeneous linear or substantially linear interpolymers; compatibility with a wide range of other polymers, tackifiers, and plasticizers, particularly waxes; and improved adhesion to polyolefin substrates such as polyolefin based containers and films. The adhesive composition of the present invention is also surmised to be repulpable and be able to be used at lower coating weights due to its low density, as well as be resistant to degradation caused by exposure to ultraviolet radiation.

20
The adhesive of the present invention is useful for a variety of articles such as tapes, labels, disposables, including disposable diapers and feminine napkins, as well as for bookbinding, packaging, and skin attachment adhesives for medical tapes and devices. Improved adhesion to films such as low density polyethylene (LDPE), high density polyethylene (HDPE), shrink wrap and particularly films prepared from homogeneous ethylene polymers, in combination with good spray properties, allows the adhesive compositions of the present invention to be particularly useful for the nonwoven industry in the manufacture of disposable diapers, feminine napkins, and surgical drapes.

25
30
In another preferred embodiment, homogeneous ethylene polymers have further been found to be useful alone or in combination with other ingredients such as tackifiers and waxes as a coextrusion coating or a thermoplastic packaging film which is meltable and blendable with the adhesive composition, such as a batch inclusion bag. This aspect is particularly advantageous when the polymer of the adhesive composition, the coextrusion coating, and/or the thermoplastic packaging film are of the same polymer chemistry, insuring mutual compatibility.

These and other embodiments are more fully described in the following detailed description.

The adhesives of the invention comprise at least one homogeneous ethylene/ α -olefin interpolymer which is an interpolymer of ethylene and at least one C_3 - C_{20} α -olefin. The term "interpolymer" is used herein to indicate a copolymer, or a terpolymer, or a higher order polymer. That is, at least one other comonomer is polymerized with ethylene to make the interpolymer.

The homogeneous ethylene/ α -olefin interpolymer is a homogeneous linear or substantially linear ethylene/ α -olefin interpolymer. By the term "homogenous", it is meant that any comonomer is randomly distributed within a given interpolymer molecule and substantially all of the interpolymer molecules have the same ethylene/comonomer ratio within that interpolymer. The melting peak of homogeneous linear and substantially linear ethylene polymers, as obtained using differential scanning calorimetry, will broaden as the density decreases and/or as the number average molecular weight decreases. However, unlike heterogeneous polymers, when a homogeneous polymer has a melting peak greater than 115°C (such as is the case of polymers having a density greater than 0.940 g/cm³), it does not additionally have a distinct lower temperature melting peak.

In addition or in the alternative, the homogeneity of the polymer may be described by the SCBDI (Short Chain Branching Distribution Index) or CDBI (Composition Distribution Breadth Index), which are defined as the weight percent of the polymer molecules having a comonomer content within 50 percent of the median total molar comonomer content. The SCBDI of a polymer is readily calculated from data obtained from techniques known in the art, such as, for example, temperature rising elution fractionation (abbreviated herein as "TREF"), which is described, for example, in Wild et al., Journal of Polymer Science, Poly. Phys. Ed., Vol. 20, p. 441 (1982), in U.S. Patent 4,798,081 (Hazlitt et al.), or in U.S. Patent 5,089,321 (Chum et al.). The SCBDI or CDBI for the homogeneous ethylene/ α -olefin interpolymers useful in the invention is preferably greater than 50 percent, more preferably greater

than 70 percent, with SCBDI's and CDBI of greater than 90 percent being easily attained.

The homogeneous ethylene/ α -olefin interpolymers useful in the invention are characterized as having a narrow molecular weight distribution (M_w/M_n). For the
5 homogeneous ethylene/ α -olefins useful in the adhesives of the invention, the M_w/M_n is from 1.5 to 2.5, preferably from 1.8 to 2.2, most preferably about 2.0.

Substantially linear ethylene interpolymers are homogeneous interpolymers having long chain branching. Due to the presence of such long chain branching, substantially linear ethylene interpolymers are further characterized as having a melt
10 flow ratio (I_1/I_2) which may be varied independently of the polydispersity index, and the like, the molecular weight distribution M_w/M_n . This feature accords substantially linear ethylene polymers with a high degree of processability despite a narrow molecular weight distribution.

It is noted that substantially linear interpolymers useful in the invention differ
15 from low density polyethylene prepared in a high pressure process. In one regard, whereas low density polyethylene is an ethylene homopolymer having a density of from 0.900 to 0.935 g/cm³, the homogeneous linear and substantially linear interpolymers useful in the invention require the presence of a comonomer to reduce the density to the range of from 0.900 to 0.935 g/cm³.

The long chain branches of substantially linear ethylene interpolymers have the
20 same comonomer distribution as the interpolymers backbone and can be as long as about the same length as the length of the interpolymers backbone. When a substantially linear ethylene/ α -olefin interpolymers is employed in the practice of the invention, such interpolymers will be characterized as having an interpolymers backbone
25 substituted with from 0.01 to 3 long chain branches per 1000 carbons.

Methods for determining the amount of long chain branching present, both qualitatively and quantitatively, are known in the art.

For qualitative methods for determining the presence of long chain branching, see, for example, U.S. Patent Nos. 5,272,236 and 5,278,272. As set forth therein, a gas
30 extrusion rheometer (GER) may be used to determine the rheological processing index (PI), the critical shear rate at the onset of surface melt fracture, and the critical shear

stress at the onset of gross melt fracture, which in turn indicate the presence or absence of long chain branching as set forth below.

The gas extrusion rheometer useful in the determination of rheological processing index (PI), the critical shear rate at the onset of surface melt fracture, and the critical shear stress at the onset of gross melt fracture, is described by M. Shida, R. N. Shroff, and L. V. Cancio in *Polymer Engineering Science*, Vol. 17, No. 11, p. 770 (1977), and in "Rheometers for Molten Plastics" by John Dealy, published by Van Nostrand Reinhold co. (1982) on pp. 97-99. GER experiments are performed at a temperature of 190°C, at nitrogen pressures between 250 and 5500 psig (between 1.72 and 37.9 MPa) using a 0.0754 mm diameter, 20:1 L/D die with an entrance angle of 180°.

For substantially linear ethylene interpolymers, the PI is the apparent viscosity (in kpoise) of a material measured by GER at an apparent shear stress of 2.15×10^6 dynes/cm² (0.215 MPa). Substantially linear ethylene interpolymers useful in the invention will have a PI in the range of 0.01 kpoise to 50 kpoise, preferably 15 kpoise or less. Substantially linear ethylene interpolymers have a PI which is less than or equal to 70 percent of the PI of a linear ethylene interpolymers (either a Ziegler polymerized polymer or a homogeneous linear ethylene interpolymers) having the same comonomer or comonomers, and having an I_2 , M_w/M_n , and density, each of which is within 10 percent of that of the substantially linear ethylene interpolymers.

An apparent shear stress versus apparent shear rate plot may be used to identify the melt fracture phenomena and to quantify the critical shear rate and critical shear stress of ethylene polymers. According to Ramamurthy, in the *Journal of Rheology*, 30(2), 1986, pp. 337-357, above a certain critical flow rate, the observed extrudate irregularities may be broadly classified into two main types: surface melt fracture and gross melt fracture.

Surface melt fracture occurs under apparently steady flow conditions and ranges in detail from loss of specular film gloss to the more severe form of "sharkskin." Herein, as determined using the above-described gas extrusion rheometer, the onset of surface melt fracture is characterized as the beginning of losing extrudate gloss at which the surface roughness of the extrudate can only be detected by magnification at

40 times. The critical shear rate at the onset of surface melt fracture for a substantially linear ethylene interpolymer is at least 50 percent greater than the critical shear rate at the onset of surface melt fracture for a linear ethylene polymer having the same comonomer or comonomers and having an I_2 , M_w/M_n and density within ten percent
 5 of that of the substantially linear ethylene polymer.

Gross melt fracture occurs at unsteady extrusion flow conditions and ranges from regular (alternating rough and smooth, helical, etc.) to random distortions. The critical shear stress at the onset of gross melt fracture of substantially linear ethylene interpolymers, especially those having a density greater than 0.910 g/cm^3 , is greater
 10 than $4 \times 10^6 \text{ dynes/cm}^2$ (0.4 MPa)..

The presence of long chain branching may further be qualitatively determined by the Dow Rheology Index (DRI), which expresses a polymer's "normalized relaxation time as the result of long chain branching." (See, S. Lai and G. W. Knight, ANTEC '93 Proceedings, INSITE™ Technology Polyolefins (SLEP)- New Rules in
 15 the Structure/Rheology Relationship of Ethylene α -Olefin Copolymers, New Orleans, La., May 1993. DRI values range from 0 for polymers which do not have any measurable long chain branching, such as Tafmer™ products available from Mitsui Petrochemical Industries and Exact™ products available from Exxon Chemical company) to about 15, and are independent of melt index. In general, for low to
 20 medium pressure ethylene polymers, particular at lower densities, DRI provides improved correlations to melt elasticity and high shear flowability relative to correlations of the same attempted with melt flow ratios. Substantially linear ethylene interpolymers will have a DRI of preferably at least 0.1, more preferably at least 0.5, and most preferably at least 0.8.

25 DRI may be calculated from the equation:

$$\text{DRI} = (3.652879 * \tau_0^{1.00649} / \eta_0 - 1) / 10$$

where τ_0 is the characteristic relaxation time of the interpolymer and η_0 is the zero shear viscosity of the interpolymer. Both τ_0 and η_0 are the "best fit" values to the Cross equation, and the like,

30
$$\eta / \eta_0 = 1 / (1 + (\dot{\gamma} * \tau_0)^{1-n})$$

in which n is the power law index of the material, and η and $\dot{\gamma}$ are the measured viscosity and shear rate, respectively. Baseline determination of viscosity and shear rate data are obtained using a Rheometric Mechanical Spectrometer (RMS-800) under dynamic sweep mode from 0.1 to 100 radians/second at 160°C and a gas extrusion
5 rheometer (GER) at extrusion pressures from 1,000 to 5,000 psi (6.89 to 34.5 MPa), which corresponds a shear stress of from 0.086 to 0.43 MPa, using a 0.0754 mm diameter, 20:1 L/D die at 190°C. Specific material determinations may be performed from 140 to 190°C as required to accommodate melt index variations.

For quantitative methods for determining the presence of long chain branching,
10 see, for example, U.S. Patent Nos. 5,272,236 and 5,278,272; Randall (Rev. Macromol. Chem. Phys., C29 (2&3), p. 285-297), which discusses the measurement of long chain branching using ^{13}C nuclear magnetic resonance spectroscopy, Zimm, G.H. and Stockmayer, W.H., J. Chem. Phys., 17, 1301 (1949); and Rudin, A., Modern Methods of Polymer Characterization, John Wiley & Sons, New York (1991) pp. 103-112,
15 which discuss the use of gel permeation chromatography coupled with a low angle laser light scattering detector (GPC-LALLS) and gel permeation chromatography coupled with a differential viscometer detector (GPC-DV).

A. Willem deGroot and P. Steve Chum, both of The Dow Chemical Company, at the October 4, 1994 conference of the Federation of Analytical Chemistry and
20 Spectroscopy Society (FACSS) in St. Louis, Missouri, presented data demonstrating that GPC-DV is a useful technique for quantifying the presence of long chain branches in substantially linear ethylene polymers. In particular, deGroot and Chum found that the presence of long chain branches in substantially linear ethylene polymers correlated well with the level of long chain branches measured using ^{13}C NMR.

25 Further, deGroot and Chum found that the presence of octene does not change the hydrodynamic volume of the polyethylene samples in solution and, as such, one can account for the molecular weight increase attributable to octene short chain branches by knowing the mole percent octene in the sample. By deconvoluting the contribution to molecular weight increase attributable to 1-octene short chain branches,
30 deGroot and Chum showed that GPC-DV may be used to quantify the level of long chain branches in substantially linear ethylene/octene copolymers.

deGroot and Chum also showed that a plot of $\log(I_2, \text{melt index})$ as a function of $\log(\text{GPC weight average molecular weight})$, as determined by GPC-DV, illustrates that the long chain branching aspects (but not the extent of long chain branching) of substantially linear ethylene polymers are comparable to those of high pressure, highly branched low density polyethylene (LDPE) and are clearly distinct from heterogeneously branched ethylene polymers produced using Ziegler-type catalysts (such as linear low density polyethylene and ultra low density polyethylene) as well as from homogeneous linear ethylene polymers (such as Tafmer™ products available from Mitsui Petrochemical Industries and Exact™ products available from Exxon Chemical Company).

The first polymer will be an interpolymer of ethylene with at least one comonomer selected from the group consisting of C₃-C₂₀ α -olefins, non-conjugated dienes, and cycloalkenes. Exemplary C₃-C₂₀ α -olefins include propylene, isobutylene, 1-butene, 1-hexene, 4-methyl-1-pentene, 1-heptene, and 1-octene. Preferred C₃-C₂₀ α -olefins include 1-butene, 1-hexene, 4-methyl-1-pentene, 1-heptene, and 1-octene, more preferably 1-hexene and 1-octene. Exemplary cycloalkenes include cyclopentene, cyclohexene, and cyclooctene. The non-conjugated dienes suitable as comonomers, particularly in the making of ethylene/ α -olefin/diene terpolymers, are typically non-conjugated dienes having from 6 to 15 carbon atoms.

Representative examples of suitable non-conjugated dienes include:

- (a) Straight chain acyclic dienes such as 1,4-hexadiene; 1,5-heptadiene; and 1,6-octadiene;
- (b) Branched chain acyclic dienes such as 5-methyl-1,4-hexadiene; 3,7-dimethyl-1,6-octadiene; and 3,7-dimethyl-1,7-octadiene;
- (c) Single ring alicyclic dienes such as 4-vinylcyclohexene; 1-allyl-4-isopropylidene cyclohexane; 3-allylcyclopentene; 4-allylcyclohexene; and 1-isopropenyl-4-butenylcyclohexene;
- (d) Multi-ring alicyclic fused and bridged ring dienes such as dicyclopentadiene; alkenyl, alkylidene, cycloalkenyl, and cycloalkylidene norbornenes, such as 5-methylene-2-norbornene; 5-methylene-6-methyl-2-norbornene; 5-methylene-6,6-dimethyl-2-

norbornene; 5-propenyl-2-norbornene; 5-(3-cyclopentenyl)-2-norbornene; 5-ethylidene-2-norbornene; and 5-cyclohexylidene-2-norbornene.

One preferred conjugated diene is piperylene. The preferred dienes are
5 selected from the group consisting of 1,4-hexadiene; dicyclopentadiene; 5-ethylidene-2-norbornene; 5-methylene-2-norbornene; 7-methyl-1,6 octadiene; piperylene; and 4-vinylcyclohexene.

The molecular weight of the ethylene/ α -olefin interpolymer will be selected on the basis of the desired performance attributes of the adhesive formulation. Typically,
10 however, the ethylene/ α -olefin interpolymer will preferably have a number average molecular weight of at least 3,000, preferably at least 5,000. Typically, the ethylene/ α -olefin interpolymer will preferably have a number average molecular weight of no more than 100,000, more preferably no more than 60,000, and even more preferably less than 40,000.

15 When the ethylene/ α -olefin interpolymer has an ultra-low molecular weight, and the like, a number average molecular weight less than 11,000, the ethylene/ α -olefin interpolymer leads to a low polymer and formulation viscosity but is characterized by a peak crystallization temperature which is greater than that of corresponding higher molecular weight materials of the same density. In pressure
20 sensitive adhesive applications, the increase in peak crystallization temperature translates to an increased heat resistance. Ultra-low molecular weight ethylene/ α -olefin interpolymers are more fully described below.

The density of the ethylene/ α -olefin interpolymer will likewise be selected on the basis of the desired performance attributes of the adhesive formulation. Typically,
25 however, the ethylene/ α -olefin interpolymer will have a density of at least 0.850 g/cm³, preferably at least 0.860, and more preferably at least 0.870 g/cm³. Typically, the ethylene/ α -olefin interpolymer will have a density of no more than 0.965 g/cm³, preferably no more than 0.900 g/cm³, more preferably no more than 0.890 g/cm³, and even more preferably no more than 0.880 g/cm³, and most preferably no more than
30 0.875 g/cm³.

The ethylene/ α -olefin interpolymer will be present in the adhesives of the invention in an amount greater than 5, and preferably greater than 10 weight percent. The ethylene/ α -olefin interpolymer will typically be present in the adhesive of the invention in an amount of not more than 95, preferably not more than 80, and more preferably not more than 70 weight percent.

The adhesive may comprise a single homogeneous ethylene/ α -olefin interpolymer. In such an embodiment, the homogeneous ethylene/ α -olefin interpolymer will preferably have a density ranging from 0.865 g/cm³ to 0.885 g/cm³. When it is desired to prepare an adhesive formulation with a minimal concentration of the homogeneous linear or substantially linear interpolymer, and the like, adhesive formulations containing less than 30 weight percent, preferably less than 25 weight percent of the homogeneous ethylene/ α -olefin interpolymer, the melt index (I₂ at 190° C) of the homogeneous linear or substantially linear interpolymer will be preferably 50 or less, more preferably 30 or less, and most preferably less than 10 g/10 min. It is believed that adhesive compositions comprising as little as 5 weight percent of the homogeneous ethylene/ α -olefin interpolymer having a melt index less than 0.5 g/10 min. would yield an advantageous performance.

In the case of pressure sensitive adhesives, preferred adhesives will comprise from 5 to 45 weight percent, preferably from 10 to 30, more preferably from 15 to 25 weight percent of a single homogeneous ethylene/ α -olefin interpolymer. For other applications, for example packaging, the homogeneous linear or substantially linear interpolymer will preferably be employed at concentrations greater than 30 weight percent and have a melt index of 500 g/10 min or less.

In another embodiment, the first homogeneous ethylene/ α -olefin interpolymer may be blended with a second homogeneous ethylene/ α -olefin interpolymer, wherein the first and second interpolymers differ in number average molecular weight by at least 5000, preferably at least 10,000, and more preferably at least 20,000. In this embodiment, the combination of the lower molecular weight and higher molecular weight components will tend to yield an intermediate storage modulus at 25°C and an improved probe tack.

In addition or in the alternative, the first homogeneous ethylene/ α -olefin interpolymer may be blended with a second homogeneous ethylene/ α -olefin interpolymer, wherein the first and second interpolymers differ in density by at least 0.005 g/cm³, preferably by at least 0.01 g/cm³. In this embodiment, particularly in the case of pressure sensitive adhesives, as the density differential increases, the relative proportion of the higher density interpolymer will typically decrease, as the increased levels of crystallinity would otherwise tend to decrease storage modulus at 25°C and probe tack to levels which would render them unsuitable for use as pressure sensitive adhesives.

In one preferred embodiment, the adhesive will comprise a blend of two homogeneous ethylene/ α -olefin, wherein the first interpolymer having a density of 0.870 g/cm³ or less and the second interpolymer having density greater than 0.900 g/cm³. When high cohesive strength is desired, the first and second homogeneous linear or substantially linear interpolymer, will preferably both have relatively low melt indices, and the like, an I₂ of less than 30 g/10 min. In contrast, for lower viscosity adhesive compositions, especially those which are sprayable at temperatures less than 325°F (163°C), the second homogeneous ethylene/ α -olefin interpolymer will have a greater density than the first homogeneous ethylene/ α -olefin interpolymer, and will preferably have a melt index greater than 125, more preferably greater than 500, and most preferably greater than 1000 g/10 min.

Homogeneously branched linear ethylene/ α -olefin interpolymers may be prepared using polymerization processes (for example, as described by Elston in USP 3,645,992) which provide a homogeneous short chain branching distribution. In his polymerization process, Elston uses soluble vanadium catalyst systems to make such polymers. However, others such as Mitsui Petrochemical Company and Exxon Chemical Company have used so-called single site catalyst systems to make polymers having a homogeneous linear structure. U.S. Patent No. 4,937,299 to Ewen et al. and U.S. Patent No. 5,218,071, to Tsutsui et al. disclose the use of catalyst systems based on hafnium for the preparation of homogeneous linear ethylene polymers.

Homogeneous linear ethylene/ α -olefin interpolymers are currently available from

Mitsui Petrochemical Company under the trade name "Tafmer" and from Exxon Chemical Company under the trade name "Exact".

Substantially linear ethylene/ α -olefin interpolymers are available from The Dow Chemical Company as Affinity™ polyolefin plastomers and Engage™ polyolefin elastomers. Substantially linear ethylene/ α -olefin interpolymers may be prepared in accordance with the techniques described in U.S. Patent No. 5,272,236 and in U.S. Patent No. 5,278,272.

Ultra-low molecular weight polymers may be made in accordance with the Examples herein and with the procedures set forth below.

The first polymer may be suitably prepared using a constrained geometry metal complex, such as are disclosed in U.S. Application Serial No. 545,403, filed July 3, 1990 (EP-A-416,815); U.S. Application Serial No. 702,475, filed May 20, 1991 (EP-A-514,828); as well as US-A-5,470,993, 5,374,696, 5,231,106, 5,055,438, 5,057,475, 5,096,867, 5,064,802, and 5,132,380. In U.S. Serial Number 720,041, filed June 24, 1991, (EP-A-514,828) certain borane derivatives of the foregoing constrained geometry catalysts are disclosed and a method for their preparation taught and claimed. In US-A 5,453,410 combinations of cationic constrained geometry catalysts with an alumoxane were disclosed as suitable olefin polymerization catalysts.

Suitable activating cocatalysts and activating techniques have been previously taught with respect to different metal complexes in the following references: EP-A-277,003, US-A-5,153,157, US-A-5,064,802, EP-A-468,651 (equivalent to U. S. Serial No. 07/547,718), EP-A-520,732 (equivalent to U. S. Serial No. 07/876,268), WO 95/00683 (equivalent to U.S. Serial No. 08/82,201), and EP-A-520,732 (equivalent to U. S. Serial No. 07/884,966 filed May 1, 1992).

Catalysts found to be particularly suitable in the preparation of substantially linear ethylene/ α -olefin interpolymers include, for instance, the catalysts described in the Examples set forth below, as activated by trispentafluorophenylborane and triisobutylaluminum modified methylalumoxane cocatalysts.

The molar ratio of metal complex: activating cocatalyst employed preferably ranges from 1:1000 to 2:1, more preferably from 1:5 to 1.5:1, most preferably from 1:2 to 1:1. In the preferred case in which a metal complex is activated by

tris(pentafluorophenyl)borane and triisobutylaluminum modified methylalumoxane, the titanium:boron:aluminum molar ratio is typically from 1:10:50 to 1:0.5:0.1, most typically from about 1:3:5.

A support, especially silica, alumina, or a polymer (especially poly(tetrafluoroethylene) or a polyolefin) may be employed, and desirably is employed when the catalysts are used in a gas phase polymerization process. The support is preferably employed in an amount to provide a weight ratio of catalyst (based on metal):support from 1:100,000 to 1:10, more preferably from 1:50,000 to 1:20, and most preferably from 1:10,000 to 1:30. In most polymerization reactions the molar ratio of catalyst:polymerizable compounds employed is from 10^{-12} :1 to 10^{-1} :1, more preferably from 10^{-9} :1 to 10^{-5} :1.

At all times, the individual ingredients as well as the recovered catalyst components must be protected from oxygen and moisture. Therefore, the catalyst components and catalysts must be prepared and recovered in an oxygen and moisture free atmosphere. Preferably, therefore, the reactions are performed in the presence of a dry, inert gas such as, for example, nitrogen.

The polymerization may be carried out as a batchwise or a continuous polymerization process, with continuous polymerizations processes being required for the preparation of substantially linear polymers. In a continuous process, ethylene, comonomer, and optionally solvent and diene are continuously supplied to the reaction zone and polymer product continuously removed therefrom.

In general, the first polymer may be polymerized at conditions for Ziegler-Natta or Kaminsky-Sinn type polymerization reactions, that is, reactor pressures ranging from atmospheric to 3500 atmospheres. The reactor temperature should be greater than 80°C, typically from 100°C to 250°C, and preferably from 100°C to 150°C, with temperatures at the higher end of the range, and the like, temperatures greater than 100°C favoring the formation of lower molecular weight polymers.

In conjunction with the reactor temperature, the hydrogen:ethylene molar ratio influences the molecular weight of the polymer, with greater hydrogen levels leading to lower molecular weight polymers. When the desired polymer has an I_2 of 1 g/10 min, the hydrogen:ethylene molar ratio will typically be 0:1. When the desired

polymer has an I₂ of 1000 g/10 min., the hydrogen:ethylene molar ratio will typically be from 0.45:1 to 0.7:1. The upper limit of the hydrogen:ethylene molar ratio is from 2.2 to 2.5:1.

5 Generally the polymerization process is carried out with a differential pressure of ethylene of from 10 to 1000 psi (70 to 7000 kPa), most preferably from 40 to 60 psi (30 to 300 kPa). The polymerization is generally conducted at a temperature of from 80 to 250°C, preferably from 90 to 170°C, and most preferably from greater than 95°C to 140°C.

10 In most polymerization reactions the molar ratio of catalyst:polymerizable compounds employed is from 10⁻¹²:1 to 10⁻¹:1, more preferably from 10⁻⁹:1 to 10⁻⁵:1. Solution polymerization conditions utilize a solvent for the respective components of the reaction. Preferred solvents include mineral oils and the various hydrocarbons which are liquid at reaction temperatures. Illustrative examples of useful solvents include alkanes such as pentane, iso-pentane, hexane, heptane, octane
15 and nonane, as well as mixtures of alkanes including kerosene and Isopar-E™, available from Exxon Chemicals Inc.; cycloalkanes such as cyclopentane and cyclohexane; and aromatics such as benzene, toluene, xylenes, ethylbenzene and diethylbenzene.

20 The solvent will be present in an amount sufficient to prevent phase separation in the reactor. As the solvent functions to absorb heat, less solvent leads to a less adiabatic reactor. The solvent:ethylene ratio (weight basis) will typically be from 2.5:1 to 12:1, beyond which point catalyst efficiency suffers. The most typical solvent:ethylene ratio (weight basis) is in the range of from 5:1 to 10:1.

25 The ethylene/α-olefin interpolymer may alternatively be prepared in a gas phase polymerization process, using the catalysts as described above as supported in an inert support, such as silica. The ethylene/α-olefin interpolymer may further be made in a slurry polymerization process, using the catalysts as described above as supported in an inert support, such as silica. As a practical limitation, slurry polymerizations take place in liquid diluents in which the polymer product is
30 substantially insoluble. Preferably, the diluent for slurry polymerization is one or more hydrocarbons with less than 5 carbon atoms. If desired, saturated hydrocarbons

such as ethane, propane or butane may be used in whole or part as the diluent.

Likewise the α -olefin monomer or a mixture of different α -olefin monomers may be used in whole or part as the diluent. Most preferably the diluent comprises in at least major part the α -olefin monomer or monomers to be polymerized.

5 Concerning the Presence of Modifying Polymers.

Depending on the intended end use for the adhesive, it is often desirable to add at least one compatible polymer in addition to the homogeneous ethylene/ α -olefin interpolymer at concentrations up to 25 percent by weight to increase the cohesive strength, improve the sprayability, modify the open time, increase the flexibility, etc.

10 This modifying polymer may be any compatible elastomer, such as a thermoplastic block copolymer, a polyamide, an amorphous or crystalline polyolefin such as polypropylene, polybutylene or polyethylene wherein M_w is greater than 3000; an ethylenic copolymer such as ethylene-vinyl acetate (EVA), ethylene-methyl acrylate, or a mixture thereof. Surprisingly, the homogeneous ethylene/ α -olefin interpolymers
15 are also compatible with polyamides, resulting in plasticizer resistant pressure sensitive adhesives. The modifying polymer will typically be used in a relatively low concentration, so as not to detract from the improved properties of the homogeneous ethylene/ α -olefin interpolymer. A preferred modifying polymer for increasing the open time and heat resistance is a polybutene-1 copolymer such as Duraflex™ 8910
20 (Shell).

Interpolymers of ethylene are those polymers having at least one comonomer selected from the group consisting of vinyl esters of a saturated carboxylic acid wherein the acid moiety has up to 4 carbon atoms, unsaturated mono- or dicarboxylic acids of 3 to 5 carbon atoms, a salt of the unsaturated acid, esters of the unsaturated
25 acid derived from an alcohol having 1 to 8 carbon atoms, and mixtures thereof.

Terpolymers of ethylene and these comonomers are also suitable. Ionomers, which are completely or partially neutralized copolymers of ethylene and the acids described above, are discussed in more detail in U.S. Patent 3,264,272. In addition, terpolymers of ethylene/vinyl acetate/carbon monoxide or ethylene/methyl acrylate/carbon
30 monoxide containing up to 15 weight percent carbon monoxide may also be employed.

The ethylene to unsaturated carboxylic comonomer weight ratio is preferably from 95:5 to 40:60, more preferably from 90:10 to 45:50, and even more preferably from 85:15 to 60:40. The melt index (I_2 at 190°C) of these modifying interpolymers of ethylene may range from 0.1 to 150, preferably from 0.3 to 50, and more preferably
5 from 0.7 to 10 g/10 min. Physical properties, principally elongation, are known to decline to lower levels when the ethylene copolymer melt index is above 30 g/10 min.

Suitable ethylene/unsaturated carboxylic acid, salt and ester interpolymers include ethylene/vinyl acetate (EVA) including, but not limited to, the stabilized EVA described in U.S. Patent 5,096,955, incorporated herein by reference; ethylene/acrylic
10 acid (EAA) and its ionomers; ethylene/methacrylic acid and its ionomers; ethylene/methyl acrylate; ethylene/ethyl acrylate; ethylene/isobutyl acrylate; ethylene/n-butyl acrylate; ethylene/isobutyl acrylate/methacrylic acid and its ionomers; ethylene/n-butyl acrylate/methacrylic acid and its ionomers; ethylene/isobutyl
15 acrylate/acrylic acid and its ionomers; ethylene/n-butyl acrylate/acrylic acid and its ionomers; ethylene/methyl methacrylate; ethylene/vinyl acetate/methacrylic acid and its ionomers; ethylene/vinyl acetate/acrylic acid and its ionomers; ethylene/vinyl acetate/carbon monoxide; ethylene/methacrylate/carbon monoxide; ethylene/ n-butyl acrylate/carbon monoxide; ethylene/isobutyl acrylate/carbon monoxide; ethylene/vinyl acetate/monoethyl maleate; and ethylene/methyl acrylate/monoethyl maleate.
20 Particularly suitable copolymers are EVA; EAA; ethylene/methyl acrylate; ethylene/isobutyl acrylate; and ethylene/methyl methacrylate copolymers and mixtures thereof. Certain properties, such as tensile elongation, are taught to be improved by certain combinations of these ethylene interpolymers, as described in U.S. Patent 4,379,190. The procedures for making these ethylene interpolymers are well known in
25 the art and many are commercially available.

Concerning the tackifier.

As used herein, the term "tackifier" means any of the compositions described below which are useful to impart tack to the hot melt adhesive composition. ASTM
30 D-1878-61T defines tack as "the property of a material which enables it to form a bond of measurable strength immediately on contact with another surface".

The adhesive of the invention will comprise from 0 to 95 weight percent of a tackifying resin. Typically, and particularly when it is desired to employ less than 30 weight percent of the homogeneous ethylene/ α -olefin interpolymer, the adhesives will comprise from 10 to 75 weight percent, more typically from 20 to 60 weight percent
5 tackifier.

In the alternative, in cases where it is desirable to employ at least 30 weight percent of the homogeneous ethylene/ α -olefin interpolymer, the present invention advantageously provides adhesive formulations which contain minimal tackifier, and the like, less than 30 weight percent tackifier, preferably less than 25 weight percent
10 tackifier, more preferably less than 20 weight percent tackifier, and most preferably less than 15 weight percent tackifier. In such applications, the homogeneous ethylene/ α -olefin interpolymer will preferably be provided as a blend with a second homogeneous ethylene/ α -olefin interpolymer. In such instances, adhesives containing less than 10 weight percent tackifier, and even adhesives having no tackifier, exhibit
15 adequate tack.

In general terms, the tackifying resins useful in the adhesives of the invention comprise resins derived from renewable resources such as rosin derivatives including wood rosin, tall oil, gum rosin; rosin esters, natural and synthetic terpenes, and derivatives of such. Aliphatic, aromatic or mixed aliphatic-aromatic petroleum based
20 tackifiers are also useful in the adhesives of this invention. Representative examples of useful hydrocarbon resins includes alpha-methyl styrene resins, branched and unbranched C₅ resins, C₉ resins, C₁₀ resins, as well as styrenic and hydrogenated modifications of such. Tackifying resins range from being a liquid at 37°C to having a ring and ball softening point of
25 about 135°C. Solid tackifying resins with a softening point greater than about 100°C, more preferably with a softening point greater than about 130°C are particularly useful to improve the cohesive strength of the adhesives of the present invention, particularly when only a single homogeneous ethylene/ α -olefin interpolymer is utilized.

For the adhesives of the invention, the preferred tackifying resin is
30 predominantly aliphatic. However, tackifying resins with increasing aromatic

character are also useful, particularly when a second tackifier or mutually compatible plasticizer is employed.

Concerning the Plasticizer.

A plasticizer is broadly defined as a typically organic composition that can be added to thermoplastics, rubbers and other resins to improve extrudability, flexibility, workability, or stretchability. In preferred embodiments of the invention, the plasticizer will be provided to the adhesive in amounts up to 90 weight percent, preferably less than 30 weight percent of the adhesive. The plasticizer may be either a liquid or a solid at ambient temperature. Exemplary liquid plasticizers include hydrocarbon oils, polybutene, liquid tackifying resins, and liquid elastomers. Plasticizer oils are primarily hydrocarbon oils which are low in aromatic content and which are paraffinic or naphthenic in character. Plasticizer oils are preferably low in volatility, transparent and have as little color and odor as possible. The use of plasticizers in this invention also contemplates the use of olefin oligomers, low molecular weight polymers, vegetable oils and their derivatives and similar plasticizing liquids.

When a solid plasticizing agent is employed, it will preferably have a softening point above 60°C. It is believed that by combining the homogeneous ethylene/ α -olefin interpolymer with a suitable tackifying resin and a solid plasticizer such as a cyclohexane dimethanol dibenzoate plasticizer, the resulting adhesive composition may be applied at temperatures below 120°C, preferably below 100°C. Although a 1,4-cyclohexane dimethanol dibenzoate compound commercially available from Velsicol under the trade name Benzoflex™ 352 is exemplified, any solid plasticizer that will subsequently recrystallize in the compounded thermoplastic composition is suitable. Other plasticizers that may be suitable for this purpose are described in EP 0422 108 B1 and EP 0 410 412 B1, both assigned to H.B. Fuller Company.

Concerning Waxes.

Waxes may be usefully employed in the adhesive compositions of the present invention, particularly when the adhesive composition is intended to be relatively tack free

upon cooling and solidifying, such as for various packaging and bookbinding applications as well as foam in place gaskets. Waxes are commonly used to modify the viscosity and reduce tack at concentrations up to 60 percent by weight, preferably less than about 25 percent by weight. Waxes useful in the adhesives of the present invention include paraffin waxes, microcrystalline waxes, Fischer-Tropsch, polyethylene and by-products of polyethylene wherein M_w is less than 3000. More preferably, the concentration of wax is less than 35 percent by weight for high melt point waxes. At wax concentrations above 35 percent by weight, paraffin waxes are typically used.

Also suitable are ultra-low molecular weight ethylene/ α -olefin interpolymers prepared using a constrained geometry catalyst, and may be referred to as homogeneous waxes. Such homogeneous waxes, as well as processes for preparing such homogeneous waxes, are set forth in the Examples below. Homogeneous waxes, in contrast to paraffinic waxes and crystalline ethylene homopolymer or interpolymers waxes, will have a M_w/M_n of from 1.5 to 2.5, preferably from 1.8 to 2.2.

Homogeneous waxes will be either ethylene homopolymers or interpolymers of ethylene and a C_3 - C_{20} α -olefin. The homogeneous wax will have a number average molecular weight less than 6000, preferably less than 5000. Such homogeneous waxes will typically have a number average molecular weight of at least 800, preferably at least 1300.

Homogeneous waxes lead to a low polymer and formulation viscosity, but are characterized by peak crystallization temperatures which are greater than the peak crystallization temperatures of corresponding higher molecular weight materials of the same density. In adhesive applications, the increase in peak crystallization temperature translates to an increased heat resistance, and the like, improved creep resistance in pressure sensitive adhesives, and improved SAFT in hot melt adhesives.

Concerning the Presence of Other Additives.

As is known in the art, various other components can be added to modify the tack, color, odor, etc., of a hot melt adhesive. Additives such as antioxidants (for example, hindered phenolics (for example, IrganoxTM 1010, IrganoxTM 1076),

phosphites (for example, Irgafos™ 168)), antiblock additives, pigments, and fillers, can also be included in the formulations. It is generally preferred that the additives should be relatively inert and have negligible effects upon the properties contributed by the homogeneous linear or substantially linear interpolymer, tackifying agent, and plasticizing oil.

Rheological Performance of Adhesives as Pressure Sensitive Adhesives.

As set forth in J. Class and S. Chu, Handbook of Pressure Sensitive Adhesive Technology, Second Edition, D. Satas, 1989, pages 158-204, the requirements for pressure sensitive adhesive behavior may be defined by temperature and rate dependent viscoelastic properties of the materials and formulations.

Broadly speaking, to be a suitable pressure sensitive adhesive, the formulations must have a glass transition temperature of from -45°C to 30°C, preferably from -20°C to 25°C, as reflected by the tan δ peak temperature at 1 radian per second, as determined by DMS.

According to what has come to be known as the Dahlquist criteria, broadly speaking, to be a suitable pressure sensitive adhesive, the formulation must have a plateau shear modulus at 25°C at 1 radian per second which is between 1×10^5 and 4×10^6 dynes/cm² (0.01 to 0.4 MPa), preferably from 3×10^5 and 1×10^6 dynes/cm² (0.03 to 0.1 MPa), as determined by DMS. A material stiffer than this, and the like, a material which has a plateau shear modulus at 25°C of 1×10^7 dynes/cm² (1 MPa), will not exhibit surface tack at room temperature. A material less stiff than this, and the like, a material which has a plateau shear modulus at 25°C of 1×10^4 dynes/cm² (0.001 MPa) will lack sufficient cohesive strength to be useful.

The Dahlquist criteria are useful to identify polymers which will have utility in various pressure sensitive adhesive applications. In particular, preferred pressure sensitive adhesives for use in low peel labels will have a G' of from 3×10^5 to 1×10^6 dynes/cm² (0.03 to 0.1 MPa) and a glass transition temperature of from -50 to -30°C. Preferred pressure sensitive adhesives for use in freezer labels will have a G' of from 8×10^4 to 2×10^5 dynes/cm² (0.008 to 0.02 MPa) and a glass transition temperature of from -45 to -30°C. Preferred pressure sensitive adhesives for use in cold temperature

labels will have a G' of from 2×10^5 to 1×10^6 dynes/cm² (0.02 to 0.1 MPa) and a glass transition temperature of from -25 to -10°C. Preferred pressure sensitive adhesives for use in pressure sensitive adhesive tapes will have a G' of from 7×10^5 to 5×10^6 dynes/cm² (0.07 to 0.5 MPa) and a glass transition temperature of from -10 to 10°C. Preferred pressure sensitive adhesives for use in high peel labels will have a G' of from 2×10^5 to 6×10^5 dynes/cm² (0.02 to 0.06 MPa) and a glass transition temperature of from 0 to 10°C. Preferred pressure sensitive adhesives for use in disposables will have a G' of from 4×10^5 to 2×10^6 dynes/cm² (0.04 to 0.2 MPa) and a glass transition temperature of from 10 to 30°C.

10 Formulations Useful for Hot Melt Adhesives

The follow Table A sets forth useful and preferred weight percentages of various components of the adhesive formulations of the invention, including formulations which will be preferred when it is desirable to utilize less than 30 weight percent of the homogeneous ethylene/ α -olefin interpolymer:

15

Table A

	Hot Melt Adhesives		Pressure Sensitive Adhesives	
	Useful	Preferred	Useful	Preferred
Homogeneous ethylene/ α -olefin interpolymer	5-95	5-30	5-95	10-30
Tackifier	0-95	20-60	0-95	20-60
Plasticizer (Oil)	0	0	0-95	0-30
Plasticizer (Solid)	< 30	10-20	0-50	10-50
Wax	0-60	5-25	< 10 percent	< 5 percent

Processes for the Preparation of Hot Melt Adhesives.

The hot melt adhesives and pressure sensitive adhesives of the invention may be prepared by standard melt blending procedures. In particular, the first polymer(s), tackifier(s), and optional plasticizer(s) may be melt blended at an elevated temperature (from 150 to 200°C) under an inert gas blanket until a homogeneous mix is obtained. Any mixing

20

method producing a homogeneous blend without degrading the hot melt components is satisfactory, such as through the use of a heated vessel equipped with a stirrer.

Further, the homogeneous ethylene/ α -olefin interpolymer(s), optional tackifier(s) and optional plasticizer(s) may be provided to an extrusion coater for application to the substrate.

When the ethylene/ α -olefin interpolymer is a blend of two or more ethylene/ α -olefin interpolymers, it will be preferred to prepare the pressure sensitive adhesives using a dual reactor configuration, with one of the polymers being produced in the first reactor, the other of the polymers being produced in a second reactor, and the tackifier(s) and optional plasticizer(s) being optionally provided, typically at a point after the second reactor, via a side-arm extruder. In this embodiment, pressure sensitive adhesives can be provided in forms such as pellets, pillows, or any other desired configuration. Examples of such a process which may be adapted in accordance with the teachings of this disclosure to prepare blends of a homogenous linear (higher molecular weight or ultra-low molecular weight) or substantially linear ethylene/ α -olefin interpolymer, wax, and optional tackifier, are disclosed in WO 94/00500 and WO 94/01052.

The hot melt adhesives of the present invention can be applied by extrusion, spiral spray, meltblown, spray-splatter, screen printing, or roll coating by delivery from bulk or reservoirs capable of controlling the temperature within a range from about 250°F to about 400°F. Packaging and bookbinding applications, particularly for adhesives which are relatively tack-free upon cooling are specifically within the scope of the present invention. However, any adhesive application pertaining to bonding a paper substrate selected from the group consisting of Kraft paper, coated paper, highly filled paper, laminated paper, etc. to any other paper substrate and/or polymeric film substrate is also contemplated, especially when applied by extrusion or lamination by roll coaters.

Test Methods

Unless indicated otherwise, the following testing procedures are employed:

Density is measured in accordance with ASTM D-792. The samples are annealed at ambient conditions for 24 hours before the measurement is taken.

Melt index (I_2), is measured in accordance with ASTM D-1238, condition 190 °C/2.16 kg (formally known as "Condition (E)").

5 Molecular weight is determined using gel permeation chromatography (GPC) on a Waters 150°C high temperature chromatographic unit equipped with three mixed porosity columns (Polymer Laboratories 103, 104, 105, and 106), operating at a system temperature of 140°C. The solvent is 1,2,4-trichlorobenzene, from which 0.3 percent by weight solutions of the samples are prepared for injection. The flow rate is
10 1.0 mL/min. and the injection size is 100 microliters.

The molecular weight determination is deduced by using narrow molecular weight distribution polystyrene standards (from Polymer Laboratories) in conjunction with their elution volumes. The equivalent polyethylene molecular weights are determined by using appropriate Mark-Houwink coefficients for polyethylene and
15 polystyrene (as described by Williams and Word in Journal of Polymer Science, Polymer Letters, Vol. 6, (621) 1968, incorporated herein by reference) to derive the following equation:

$$M_{\text{polyethylene}} = a * (M_{\text{polystyrene}})^b.$$

In this equation, $a = 0.4316$ and $b = 1.0$. Weight average molecular weight,
20 M_w , is calculated in the usual manner according to the following formula: $M_w = \sum w_i * M_i$, where w_i and M_i are the weight fraction and molecular weight, respectively, of the i th fraction eluting from the GPC column.

Fineline & Spray

	Adjust the hot melt applicator and laminator to proper setting.	
25	Nip Pressure	15 psi (0.1 MPa)
	Spiral Spray	4 mg/in ² (26 mg/cm ²)
	Fineline	1.4 mg/in (3.6 mg/cm)
	Web Speed	400-500 ft/min (120-150meters/min)
30	Air Temp.	50° F (10°C) above application temp

Nozzle Distance from Substrate 30-60 mm

Prepare fineline and spray bonds using the settings indicated above. During the run, drop eight to ten 2 inch by 8 inch (5 cm by 20 cm) strips of release paper cross directional across the web to serve as starting points for the T-peel evaluation. Cut 10 samples one bead or one spray spiral in width by 3 inches (7.6 cm) in length. Run T-peels on a slip/peel tester, Instron or other suitable measuring device at 12 inches (30 cm) per minute Report the average of 10 samples.

T-peels

This test method describes how to measure the removal force of an adhesive surface bonded to a fabric substrate.

Material and Equipment:

1. Mechanical roll-down device with 4.5 pound (2 kg) roller.
Available through: Engineering Service, Glenview IL 60025
2. Slip Peel Tester
Available though: Instrumentors, Inc., Cleveland, OH 44136

The first step is to prepare hot melt coated adhesive films on Mylar or polyolefin film using a suitable coating device at an appropriate application temperature. During preparation of the adhesive film, the adhesive surface is covered with release paper to facilitate handling. The coat weight is checked targeting 25 g/m² +/- 3 g/m².

The adhesive coated films are cut into 1 inch (2.5 cm) wide strips which are 4 inches (10 cm) in length in the machine direction. At one end of each strip, fold approximately ¼ inch (0.6 cm) of the strip onto itself to create a grip. Remove the release paper and place the adhesive surface of one 1 inch (2.5 cm) wide strip onto knit cotton test kit to form a composite. Place the composite on the mechanical roll-down device, and allow the roller two passes over the sample, one forward and one back. A timer is activated and the sample is placed into the jaws of the slip-peel tester. The 1 inch (2.5 cm) wide strip is placed into the mobile jaw and the fabric is placed in the

stationary jaw. No more than 1 minute after the sample has been removed from the roll-down device, the sample is peeled at 12 inches per minute (30 cm/min), averaging over 10 seconds. The procedure is repeated five times, recording the average T-peel value and noting any legging or transfer. The T-peel values are reported in grams per linear inch. In the disposable article industry, it is preferred to have T-peels in the 100-500 g range, most preferred in the 200-500 g range without adhesive transfer.

Oil Exudation

Approximately 20g of the adhesive is poured onto release paper. (Akrosil F1U-F4B Silox, 40-60#) After cooling for about 4 hours, the adhesive is evaluated for oil exudation. "Pass" indicates that the adhesive is removable from the release paper without visibly staining the release paper.

PAFT & SAFT

Each adhesive sample was coated onto Kraft paper by hand using glass rods or shims. The resultant coating is a 1 inch (2.5 cm) wide band that is about 8-10 mils or 0.008 to 0.010 inches (0.2 to 0.25 mm) thick. After conditioning the bonds at room temperature for at least 16 hours, the peel adhesion failure temperature (PAFT) and shear adhesion failure temperature (SAFT) were determined by placing samples in a programmed oven with 100 gram weights for the peel mode and 500 gram weights for the shear mode, ramping the temperature up from 25°C to 175°C at a rate of 25°C/hour. The oven automatically records the temperature at which the samples fail. The reported result is the average failure temperature of four to five bonds.

Bonding Tests

Adhesive bonds were made on various substrates using an application temperature of about 175°C, an open time of about 1 second, a set time of about 1 second, and a bead size ranging from 1/16 inch (2.5 mm) to 1/8 inch (3.1 mm). The resulting bonds were then conditioned for at least 24 hours, separated by hand and the amount of fiber tear determined. A minimum of three samples were tested for each adhesive at each condition reporting the average fiber tear.

Cloud Point

A 25 mm X 150 mm Pyrex test tube is filled 3/4 full with molten hot melt adhesive at a temperature of about 177°C. A thermometer is inserted into the molten

hot melt resting against the test tube wall. The "cloud point" is the temperature at which the thermometer markings are no longer visible when observed through the test tube wall opposite the thermometer.

Ultimate Tensile & Elongation

- 5 Prepare a 20-30 mil (0.5 - 0.7 mm) thick adhesive film free of air bubbles on a polytetrafluoroethylene or aluminum sheet. Cut 7 dogbones lengthwise from the film measuring the thickness at the gauge section. Condition the samples for at least 24 hours at 21°C and 23 to 50 percent relative humidity. Place each sample in the jaws of an Instron tensile tester or equivalent with a load cell capable of measuring a 4 pounds (1.8 kg) force +/- 1 percent. Elongate samples at a 10 inches/minute (20.5 cm/min) crosshead speed until break. Record the "Ultimate Tensile" at yield by dividing the maximum force by the cross-section area of the sample and " percent Elongation" by dividing the displacement at break by the sample length and multiply by 100. The "Ultimate Tensile" and " percent Elongation" are an average of at least five samples.

15 Cold Crack

- Prepare several 1 inch by 3 inch (2.5 cm by 7.6 cm) adhesive films free of air bubbles which are 20-30 mils (0.5 - 0.7 mm) in thickness. Place three films individually over the v-shaped base of a cold crack apparatus which consists of a stand with an interlocking pressure bar. The stand is 3 inches (7.6 cm) by 0.75 inch (1.9 cm) wide and 12 inches (30 cm) long. A 90° angle is cut squarely ½ inch (1.3 cm) deep into the top surface. Place the pressure bar, which is also cut at a 90° angle, into the gap of the stand. This test is repeated lowering the temperature at 5°F (3°C) increments with a new film sample for each temperature until the film cracks. The recorded "Cold Crack" is an average of at least 2 samples.

25 Melt Viscosity

- Melt viscosity is determined in accordance with the following procedure using a Brookfield Laboratories DVII+ Viscometer in disposable aluminum sample chambers. The spindle used is a SC-31 hot-melt spindle, suitable for measuring viscosities in the range of from 10 to 100,000 centipoise. A cutting blade is employed to cut samples into pieces small enough to fit into the 1 inch (2.5 cm) wide and 5 inches (13 cm) long sample chamber. The sample is placed in the chamber, which is

in turn inserted into a Brookfield Thermosel and locked into place with bent needle-nose pliers. The sample chamber has a notch on the bottom that fits the bottom of the Brookfield Thermosel to ensure that the chamber is not allowed to turn when the spindle is inserted and spinning. The sample is heated to 350°F (177°C), with
5 additional sample being added until the melted sample is about 1 inch (2.5 cm) below the top of the sample chamber. The viscometer apparatus is lowered and the spindle submerged into the sample chamber.

Lowering is continued until brackets on the viscometer align on the Thermosel. The viscometer is turned on, and set to a shear rate which leads to a torque reading in
10 the range of 30 to 60 percent. Readings are taken every minute for about 15 minutes, or until the values stabilize, which final reading is recorded.

G', G'', and Peak Tan Delta

G', G'', and peak tan delta, are determined as follows. The samples are
15 examined using melt rheology techniques on a Rheometrics RDA-II Dynamic Analyzer. The Temperature-Step mode is used utilizing the 7.9 mm diameter parallel plates geometry. The sweep is run from approximately -70°C to 250°C at 5°C per step with 30 seconds equilibration delay at each step. The oscillatory frequency is 1
20 radian/second with an autostrain functions of 0.1 percent strain initially, increasing in positive 100 percent adjustments when ever the torque decreased to 10 gram-centimeters. The maximum strain is set at 26 percent. The autotension function is used in the compression direction with a force of -3, sensitivity at 15, and switching occurring at 100 dynes/cm² (10 Pa). The plates are used with an initial gap of 1.5 mm
25 at 160°C (the sample aliquots are inserted in the RDS-II at 160°C). The "HOLD" function is engaged at 160°C and the instrument was cooled to -70°C and the test started (the "HOLD") function corrects for the thermal expansion or contraction of the test chamber is heated or cooled). The Samples are maintained in a nitrogen environment throughout the analyses to minimize oxidative degradation. Data reduction and manipulation are accomplished by the Rheometrics, Inc. RHIOS
30 computer programs (version 4.4.0). The computer software plots G' (the dynamic

storage modulus of the sample), G'' (the dynamic loss modulus of the sample), $\tan \delta$ (G'/G''), and peak $\tan \delta$ (a representation of the glass transition temperature).

Probe tack

Probe tack is determined in accordance with ASTM D-2979-71, using a dwell
5 time of 10 seconds and a probe separation rate of 1 cm/sec.

TABLE OF CONTENTS FOR THE EXAMPLES

	I.	Hot Melt Adhesive Examples
	-	Catalyst Preparation
5	-	Polymerization of ultra-low molecular weights polymers and waxes.
	-	Table One - Polymers A-D and Waxes 1-3 Polymerization Conditions.
	-	Table Two - Polymers E-F and Wax 4 Polymerization Conditions.
	-	Hot Melt Adhesive Examples
10	-	Table Three - Examples HMA-1 to HMA-9
	-	Table Four - Examples HMA-10 to HMA-15
	-	Table Five - Examples HMA-16 to HMA-24
	-	Examples 25 and 26
	II.	Hot Melt Pressure Sensitive Adhesive Examples
15	-	Preparation of Adhesives
	-	Table Six - Examples PSA-27 TO PSA-32
	-	Table Seven - Examples PSA-33 to PSA-34
	III.	Application Specific Adhesive Examples
	-	Tables Eight and Eight-A - Interpolymers and Formulation Components
20	-	Table Nine - Nonwoven Construction Adhesives
	-	Table Ten - Nonwoven Construction Bonding Results
	-	Table Eleven - Thermal Stability of Adhesives
	-	Table Twelve - Positioning Adhesives
	-	Table Thirteen - Additional PSA Examples
25	-	Table Fourteen - Additional Interpolymer/EVA Blends
	-	Table Fifteen - Target Bookbinding Properties
	-	Tables Sixteen A and B- Bookbinding
	-	Table Seventeen- Case and Carton Seal
	-	Tables Eighteen A,B,C - Packaging Adhesives
30	-	Tables Nineteen A to E - Interpolymer/Oil Blends
	-	Tables Twenty A and B- Interpolymer/Polyamide Blends
	-	Table Twenty-One - Insulation Bonding

I. Hot Melt Adhesive Examples

Catalyst Preparation One

Part 1: Preparation of $\text{TiCl}_3(\text{DME})_{1.5}$

5 The apparatus (referred to as R-1) was set-up in the hood and purged with nitrogen; it consisted of a 10 L glass kettle with flush mounted bottom valve, 5-neck head, polytetrafluoroethylene gasket, clamp, and stirrer components (bearing, shaft, and paddle). The necks were equipped as follows: stirrer components were put on the center neck, and the outer necks had a reflux condenser topped with gas inlet/outlet, an
10 inlet for solvent, a thermocouple, and a stopper. Dry, deoxygenated dimethoxyethane (DME) was added to the flask (approx. 5 L). In the drybox, 700 g of TiCl_3 was weighed into an equalizing powder addition funnel; the funnel was capped, removed from the drybox, and put on the reaction kettle in place of the stopper. The TiCl_3 was added over about 10 minutes with stirring. After the addition was completed,
15 additional DME was used to wash the rest of the TiCl_3 into the flask. The addition funnel was replaced with a stopper, and the mixture heated to reflux. The color changed from purple to pale blue. The mixture was heated for about 5 hours, cooled to room temperature, the solid was allowed to settle, and the supernatant was decanted from the solid. The $\text{TiCl}_3(\text{DME})_{1.5}$ was left in R-1 as a pale blue solid.

20

Part 2: Preparation of $[(\text{Me}_4\text{C}_5)\text{SiMe}_2\text{N-t-Bu}][\text{MgCl}]_2$

 The apparatus (referred to as R-2) was set-up as described for R-1, except that flask size was 30 L. The head was equipped with seven necks; stirrer in the center neck, and the outer necks containing condenser topped with nitrogen inlet/outlet,
25 vacuum adapter, reagent addition tube, thermocouple, and stoppers. The flask was loaded with 4.5 L of toluene, 1.14 kg of $(\text{Me}_4\text{C}_5\text{H})\text{SiMe}_2\text{NH-t-Bu}$, and 3.46 kg of 2 M *i*-PrMgCl in Et₂O. The mixture was then heated, and the ether allowed to boil off into a trap cooled to -78°C. After four hours, the temperature of the mixture had reached 75°C. At the end of this time, the heater was turned off and DME was added
30 to the hot, stirring solution, resulting in the formation of a white solid. The solution was allowed to cool to room temperature, the material was allowed to settle, and the

supernatant was decanted from the solid. The $[(\text{Me}_4\text{C}_5)\text{SiMe}_2\text{N-t-Bu}][\text{MgCl}]_2$ was left in R-2 as an off-white solid.

Part 3: Preparation of $[(\eta^5\text{-Me}_4\text{C}_5)\text{SiMe}_2\text{N-t-Bu}]\text{TiMe}_2$

5 The materials in R-1 and R-2 were slurried in DME (3 L of DME in R-1 and 5 L in R-2). The contents of R-1 were transferred to R-2 using a transfer tube connected to the bottom valve of the 10 L flask and one of the head openings in the 30 L flask. The remaining material in R-1 was washed over using additional DME. The mixture darkened quickly to a deep red/brown color, and the temperature in R-2 rose from
10 21°C to 32°C. After 20 minutes, 160 mL of CH_2Cl_2 was added through a dropping funnel, resulting in a color change to green/brown. This was followed by the addition of 3.46 kg of 3 M MeMgCl in THF, which caused a temperature increase from 22°C to 5 °C. The mixture was stirred for 30 minutes, then 6 L of solvent was removed under vacuum. Isopar™ E hydrocarbon (6 L) was added to the flask. This vacuum/solvent
15 addition cycle was repeated, with 4 L of solvent removed and 5 L of Isopar™ E hydrocarbon added. In the final vacuum step, an additional 1.2 L of solvent was removed. The material was allowed to settle overnight, then the liquid layer decanted into another 30 L glass kettle (R-3). The solvent in R-3 was removed under vacuum to leave a brown solid, which was re-extracted with Isopar E; this material was
20 transferred into a storage cylinder. Analysis indicated that the solution (17.23 L) was 0.1534 M in titanium; this is equal to 2.644 moles of $[(\eta^5\text{-Me}_4\text{C}_5)\text{SiMe}_2\text{N-t-Bu}]\text{TiMe}_2$. The remaining solids in R-2 were further extracted with Isopar™ E hydrocarbon, the solution was transferred to R-3, then dried under vacuum and re-extracted with Isopar™ E hydrocarbon. This solution was transferred to storage
25 bottles; analysis indicated a concentration of 0.1403 M titanium and a volume of 4.3 L (0.6032 moles $[(\eta^5\text{-Me}_4\text{C}_5)\text{SiMe}_2\text{N-t-Bu}]\text{TiMe}_2$). This gives an overall yield of 3.2469 moles of $[(\eta^5\text{-Me}_4\text{C}_5)\text{SiMe}_2\text{N-t-Bu}]\text{TiMe}_2$, or 1063 g. This is a 72 percent yield overall based on the titanium added as TiCl_3 .

Catalyst Preparation TwoPart 1: Preparation of $\text{TiCl}_3(\text{DME})_{1.5}$

The apparatus (referred to as R-1) was set-up in the hood and purged with nitrogen; it consisted of a 10 L glass kettle with flush mounted bottom valve, 5-neck head, polytetrafluorethylene gasket, clamp, and stirrer components (bearing, shaft, and paddle). The necks were equipped as follows: stirrer components were put on the center neck, and the outer necks had a reflux condenser topped with gas inlet/outlet, an inlet for solvent, a thermocouple, and a stopper. Dry, deoxygenated dimethoxyethane (DME) was added to the flask (approx. 5.2 L). In the drybox, 300 g of TiCl_3 was weighed into an equalizing powder addition funnel; the funnel was capped, removed from the drybox, and put on the reaction kettle in place of the stopper. The TiCl_3 was added over about 10 minutes with stirring. After the addition was completed, additional DME was used to wash the rest of the TiCl_3 into the flask. This process was then repeated with 325 g of additional TiCl_3 , giving a total of 625 g. The addition funnel was replaced with a stopper, and the mixture heated to reflux. The color changed from purple to pale blue. The mixture was heated for about 5 hours, cooled to room temperature, the solid was allowed to settle, and the supernatant was decanted from the solid. The $\text{TiCl}_3(\text{DME})_{1.5}$ was left in R-1 as a pale blue solid.

Part 2: Preparation of $[(\text{Me}_4\text{C}_5)\text{SiMe}_2\text{N-t-Bu}][\text{MgCl}]_2$

The apparatus (referred to as R-2) was set-up as described for R-1, except that flask size was 30 L. The head was equipped with seven necks; stirrer in the center neck, and the outer necks containing condenser topped with nitrogen inlet/outlet, vacuum adapter, reagent addition tube, thermocouple, and stoppers. The flask was loaded with 7 L of toluene, 3.09 kg of 2.17 M *i*-PrMgCl in Et_2O , 250 mL of THF, and 1.03 kg of $(\text{Me}_4\text{C}_5\text{H})\text{SiMe}_2\text{NH-t-Bu}$. The mixture was then heated, and the ether allowed to boil off into a trap cooled to -78°C . After three hours, the temperature of the mixture had reached 80°C , at which time a white precipitate formed. The temperature was then increased to 90°C over 30 minutes and held at this temperature for 2 hours. At the end of this time, the heater was turned off, and 2 L of DME was added to the hot, stirring solution, resulting in the formation of additional precipitate.

The solution was allowed to cool to room temperature, the material was allowed to settle, and the supernatant was decanted from the solid. An additional wash was done by adding toluene, stirring for several minutes, allowing the solids to settle, and decanting the toluene solution. The $[(\text{Me}_4\text{C}_5)\text{SiMe}_2\text{N-t-Bu}][\text{MgCl}]_2$ was left in R-2
5 as an off-white solid.

Part 3: Preparation of $[(\eta^5\text{-Me}_4\text{C}_5)\text{SiMe}_2\text{N-t-Bu}]\text{Ti}(\eta^4\text{-1,3-pentadiene})$

The materials in R-1 and R-2 were slurried in DME (the total volumes of the mixtures were approximately 5 L in R-1 and 12 L in R-2). The contents of R-1 were
10 transferred to R-2 using a transfer tube connected to the bottom valve of the 10 L flask and one of the head openings in the 30 L flask. The remaining material in R-1 was washed over using additional DME. The mixture darkened quickly to a deep red/brown color. After 15 minutes, 1050 mL of 1,3-pentadiene and 2.60 kg of 2.03 M n-BuMgCl in THF were added simultaneously. The maximum temperature reached in
15 the flask during this addition was 53 °C. The mixture was stirred for 2 hours, then approximately 11 L of solvent was removed under vacuum. Hexane was then added to the flask to a total volume of 22 L. The material was allowed to settle, and the liquid layer (12 L) was decanted into another 30 L glass kettle (R-3). An additional 15 liters of product solution was collected by adding hexane to R-2, stirring for 50 minutes,
20 again allowing to settle, and decanting. This material was combined with the first extract in R-3. The solvent in R-3 was removed under vacuum to leave a red/black solid, which was then extracted with toluene. This material was transferred into a storage cylinder. Analysis indicated that the solution (11.75 L) was 0.255 M in
25 titanium; this is equal to 3.0 moles of $[(\eta^5\text{-Me}_4\text{C}_5)\text{SiMe}_2\text{N-t-Bu}]\text{Ti}(\eta^4\text{-1,3-pentadiene})$ or 1095 g. This is a 74 percent yield based on the titanium added as TiCl_3 .

Polymerization of Ultra-Low Molecular Weight Polymers and Waxes

Polymers A-D and Waxes 1-3 were produced in a solution polymerization
30 process using a continuously stirred reactor. Polymers A, B, and C, and Wax 1 were each stabilized with 1250 ppm calcium stearate, 500 ppm Irganox™ 1076 hindered

polyphenol stabilizer (available from Ciba-Geigy Corporation), and 800 ppm PEPQ (tetrakis(2,4-di-t-butylphenyl)-4,4'-biphenylene diphosphonite) (available from Clariant Corporation). Polymer D and Waxes 2 and 3 were each stabilized with 500 ppm Irganox™ 1076 hindered polyphenol stabilizer, 800 ppm PEPQ, and 100 ppm water (as a catalyst kill agent).

The ethylene and the hydrogen were combined into one stream before being introduced into the diluent mixture, a mixture of C₈-C₁₀ saturated hydrocarbons, for example, ISOPAR-E hydrocarbon mixture (available from Exxon Chemical Company) and the comonomer. For polymers A, B, C, and D and for Waxes 1 and 2 the comonomer was 1-octene; Wax 3 had no comonomer. The reactor feed mixture was continuously injected into the reactor.

The metal complex and cocatalysts were combined into a single stream and were also continuously injected into the reactor. For Polymers A, B, and C and Wax 1, the catalyst was as prepared in Catalyst Preparation One set forth above. For Polymer D and Waxes 2 and 3, the catalyst was as prepared in Catalyst Preparation Two set forth above. For each Polymer and Wax, the co-catalyst was tris(pentafluorophenyl)borane, available as a 3 wt percent solution in Isopar™-E mixed hydrocarbon, from Boulder Scientific. Aluminum was provided in the form of a solution of modified methylalumoxane (MMAO Type 3A) in heptane, which is available at a 2 wt percent aluminum concentration from Akzo Nobel Chemical Inc.

Sufficient residence time was allowed for the metal complex and cocatalyst to react prior to introduction into the polymerization reactor. In each polymerization reaction, the reactor pressure was held constant at about 475 psig (3.3 MPa). Ethylene content of the reactor, in each polymerization, after reaching steady state, was maintained at the conditions specified in Table One.

After polymerization, the reactor exit stream was introduced into a separator where the molten polymer is separated from the unreacted comonomer(s), unreacted ethylene, unreacted hydrogen, and diluent mixture stream. The molten polymer was subsequently strand chopped or pelletized, and, after being cooled in a water bath or pelletizer, the solid pellets were collected. Table One describes the polymerization conditions and the resultant polymer properties.

TABLE ONE

	Polymer A	Polymer B	Polymer C	Polymer D	Wax 1	Wax 2	Wax 3
Ethylene feed (lb/hr (kg/hr))	2.0 (0.9)	2.0 (0.9)	2.0 (0.9)	3.0 (1.4)	3.0 (1.4)	3.0 (1.4)	3.0 (1.4)
Comonomer: olefin ratio (mole percent)	12.40	8.50	12.50	9.10	0.40	1.24	0.00
Hydrogen: ethylene ratio (mole percent)	0.26	0.66	1.26	0.54	1.60	2.14	2.14
Diluent: ethylene ratio (weight basis)	10.60	9.30	11.10	9.99	5.90	7.69	7.70
Catalyst metal concentration (ppm)	4	2	4	3	5	32	32
Catalyst flow rate (lb/hr (kg/hr))	0.272 (0.123)	0.386 (0.175)	0.428 (0.194)	0.450 (0.205)	0.626 (0.285)	0.304 (0.138)	0.294 (0.134)
Co-catalyst concentration (ppm)	88	44	88	88	353	1430	1430
Co-catalyst flow rate (lb/hr (kg/hr))	0.396 (0.180)	0.561 (0.254)	0.624 (0.283)	0.490 (0.223)	0.284 (0.129)	0.219 (0.100)	0.211 (0.096)
Aluminum concentration (ppm)	10	5	10	9.8	20	120.0	120.0
Aluminum flow rate (lb/hr)	0.375 (0.170)	0.528 (0.240)	0.590 (0.268)	0.468 (0.213)	0.534 (0.243)	0.323 (0.147)	0.311 (0.141)
Reactor temperature (°C)	110	110	110	110	140	110	110
Ethylene concentration in reactor exit stream (weight percent)	1.80	2.99	1.65	1.71	4.41	1.80	1.69
Polymer density (g/cm ³)	0.875	0.897	0.870	0.883	0.968	0.948	0.960
Polymer melt viscosity at 350°F (centipoise)	39,000*	5200	355	5000	395	350	512
Polymer melt index (I ₂ at 190°C)	246	1500*	16,000*	1500*	15,000*	16,000*	12,000*
Polymer Mw	30,100	15,600	7,900	16,200	7,300	6,900	7,400
Polymer Mn	17,100	8,700	4,300	8,200	3,700	3,200	3,200
Polymer Mw/Mn	1.76	1.79	1.84	1.98	1.97	2.16	2.31
Peak crystallization temperature by DSC (°C)	55.73	59.05	78.57	69.27	114.76	109.88	116.39
Peak melting temperature by DSC (°C)	68	67	91.04	81.97	127.6	120.5	131.11
Total percent crystallinity by DSC	18.94	19.55	36.3	28.18	79.62	72.81	72.84

*Calculated on the basis of melt viscosity correlations in accordance with the formula:

$$I_2 = 3.6126(10 \log(\eta) - 6.6928) - 1.1363) - 9.3185, \text{ where } \eta = \text{melt viscosity at } 350^\circ\text{F}$$

Polymers E and F and Wax 4 were produced in a solution polymerization process using a well-mixed recirculating loop reactor. Each polymer was stabilized with 2000 ppm Irganox™ 1076 hindered polyphenol stabilizer (available from Ciba-Geigy Corporation) and 35 ppm deionized water (as a catalyst kill agent).

5 The ethylene and the hydrogen (as well as any ethylene and hydrogen which were recycled from the separator, were combined into one stream before being introduced into the diluent mixture, a mixture of C₈-C₁₀ saturated hydrocarbons, for example, Isopar™-E hydrocarbon (available from Exxon Chemical Company) and the comonomer 1-octene.

10 The metal complex and cocatalysts were combined into a single stream and were also continuously injected into the reactor. The catalyst was as prepared in Catalyst Description Two set forth above; the primary cocatalyst was tri(pentafluorophenyl)borane, available from Boulder Scientific as a 3 wt percent solution in ISOPAR-E mixed hydrocarbon; and the secondary cocatalyst was modified
15 methylalumoxane (MMAO Type 3A), available from Akzo Nobel Chemical Inc. as a solution in heptane having 2 wt percent aluminum.

Sufficient residence time was allowed for the metal complex and cocatalyst to react prior to introduction into the polymerization reactor. The reactor pressure was held constant at about 475 psig (3.3 MPa).

20 After polymerization, the reactor exit stream was introduced into a separator where the molten polymer was separated from the unreacted comonomer(s), unreacted ethylene, unreacted hydrogen, and diluent mixture stream, which was in turn recycled for combination with fresh comonomer, ethylene, hydrogen, and diluent, for introduction into the reactor. The molten polymer was subsequently strand chopped or
25 pelletized, and, after being cooled in a water bath or pelletizer, the solid pellets were collected. Table Two describes the polymerization conditions and the resultant polymer properties.

TABLE TWO

	Polymer E	Polymer F	Wax 4
Ethylene fresh feed rate (lbs/hr (kg/hr))	140 (63.5)	140 (63.5)	140 (63.5)
Total ethylene feed rate (lbs/hr (kg/hr))	146.2 (66.32)	146.17 (66.30)	146.5 (66.45)
Fresh octene feed rate (lbs/hr (kg/hr))	45.4 (20.6)	49.5 (22.4)	12.67 (5.75)
Total octene feed rate (lbs/hr (kg/hr))	Not determined	112 (50.8)	32.9 (14.9)
Total octene concentration (weight percent)	Not determined	11.4	3.36
Fresh hydrogen feed rate (standard cm ³ /min.)	4025	5350	16100
Solvent and octene feed rate (lbs/hr (kg/hr))	840 (381)	839.4 (381)	840 (381)
Ethylene conversion rate (wt percent)	90.7	90.3	88.26
Reactor temperature (°C)	109.86	119.8	134.3
Feed temperature (°C)	15	15	15.3
Catalyst concentration (ppm)	70	70	70
Catalyst flow rate (lbs/hr (kg/hr))	0.725 (0.329)	1.265 (0.5738)	4.6 (2.1)
Primary cocatalyst concentration (ppm)	1200	2031	1998
Primary cocatalyst flow rate (lbs/hr (kg/hr))	2.96 (1.34)	1.635 (0.7416)	5.86 (2.66)
Titanium:boron molar ratio	2.96	3.48	2.897
Secondary cocatalyst concentration (ppm)	198	198	198
Secondary cocatalyst flow rate (lbs/hr (kg/hr))	0.718 (0.326)	1.258 (0.571)	3.7 (1.7)
Titanium:aluminum molar ratio	5	4.986	4.037
Product density (g/cm ³)	0.8926	0.8925	0.9369
Product melt viscosity at 350°F (centipoise)	12,500	4,000	400
Polymer melt index (I ₂ at 190°C)*	686*	1,900*	14,000*
Polymer M _n	12,300*	8,900*	4,700*

* Calculated on the basis of melt viscosity correlations in accordance with the formulas:

5

$$I_2 = 3.6126(10 \log(\eta) - 6.6928) / -1.1363 - 9.3185,$$

$$M_n = 10[(\log \eta + 10.46) / 3.56]$$

where η = melt viscosity at 350°F.

Polymer G was prepared as follows. To a 4 liter autoclave stirred reactor, 865.9 g of Isopar™-E hydrocarbon (available from Exxon Chemical Company) and 800.4 g 1-octene were charged. The reactor was heated to 120°C and hydrogen was added from a 75 cc cylinder. Hydrogen was added to cause a 250 psig (1.7 MPa) pressure drop in the cylinder. The reactor was then pressurized to 450 psig (3.1 MPa) of ethylene. Catalyst was added at the rate of 1 cc/min. The catalyst was as prepared in the Catalyst Preparation One set forth above. Prior to introduction into the reactor, the catalyst was mixed with the cocatalysts at a ratio of 1.5 mL of a 0.005 M solution of Catalyst Preparation One in an inert hydrocarbon such as Isopar™-E hydrocarbon mixture, 1.5 mL of a 0.015 M solution of tris(pentafluorophenyl)borane in Isopar™-E hydrocarbon mixture (a 3 wt percent solution of tris(pentafluorophenyl)borane in Isopar™-E hydrocarbon mixture is available from Boulder Scientific), 1.5 mL of a 0.05 M solution of modified methylalumoxane in Isopar™-E hydrocarbon mixture (MMAO Type 3A) (a solution of MMAO Type 3A in heptane with a 2 wt percent aluminum content is available from Akzo Nobel Chemical Inc.), and 19.5 mL of Isopar™-E hydrocarbon mixture. Ethylene was supplied on demand. The reactor temperature and pressure were set at 120°C and 450 psig (3.1 MPa), respectively. The reaction continued for 23.1 minutes. At this time, the agitation was stopped and the reactor contents transferred to a glass collection kettle. The reactor product was dried in a vacuum oven overnight. The ethylene/octene product thus prepared had a density of 0.867 g/cm³, and an I₂ at 190°C of 842 g/10 min.

Examples 1-9: HMA's comprising polymer, tackifier, wax, and antioxidant

The indicated polymer, tackifier, wax, and antioxidant were simultaneously added in the indicated amounts to a Haake Rheocord 40 mixer using a 200 gram mixing bowl maintained at about 130°C at 95 revolutions per minute. The ingredients were mixed for about 5 minutes, until they became molten.

Polymers A-C and Wax 1 were prepared by the procedures set forth above.

Polywax 2000 ethylene homopolymer is available from Petrolite, Inc. (Tulsa, OK). Polywax 2000 has a molecular weight of approximately 2000, an M_w/M_n of

approximately 1.0, a density at 16°C of about 0.97 g/cm³, and a melting point of approximately 126°C.

CP Hall 1246 paraffinic wax is available from CP Hall (Stow, OH). CP Hall 1246 paraffinic wax has a melting point of 143°F, a viscosity at 210°F of 4.2 centipoise, and a specific gravity at 73°F of 0.915.

Escorez E1310LC petroleum hydrocarbon resin is a tackifier available from Exxon Chemical Company (Houston, TX). Escorez E1310LC has a density of 0.97 g/cm³ at 64°F, a molecular weight as determined by gel permeation chromatography of 1450, a viscosity at 177°F of 300 centipoise, and an M_w/M_n of 2.1.

Foral 105 pentaerythritol ester of hydrogenated rosin is a tackifier available from Hercules Incorporated (Wilmington, DE).

Piccotac™ 115 aliphatic hydrocarbon resin is a tackifier available from Hercules Incorporated (Wilmington, DE).

Irganox™ 1010 hindered phenolic antioxidant is available from Ciba-Geigy.

Hot melt adhesives HMA-1 through HMA-9 were tested for initial viscosity and viscosity after three days, using a Brookfield viscometer at 350°F (177°C).

Hot melt adhesives HMA-3, 4, and 7 were tested for shear adhesion failure temperature (SAFT) in accordance with the following procedure. A one inch by one inch (2.5 cm by 2.5 cm) lap shear bond to case cartons using the indicated HMA in its molten state, was prepared. Samples were hung vertically in an air circulating oven at 30°C with a 500 gram weight suspended from the bottom of the strip, except in the case of HMA-7 in which a 100 gram weight was used. The oven temperature was increased by 5°C every 30 minutes until the adhesive bond failed. The shear-fail temperature was the average of three SAFT measurements.

Hot melt adhesives HMA-1 through HMA-5 were tested for low temperature adhesion in accordance with the following procedure. A one inch by one inch (2.5 cm by 2.5 cm) lap shear bond to case cartons and to 20 point boards, using the indicated HMA in its molten state, was prepared. The samples were placed in a refrigerated oven at -30°C for about 4 hours. The samples were taken from the oven one at a time and are tested for paper tear using a 0.125 inch (3 mm) mandrel.

The hot melt adhesives (HMA's) formulated in this manner are set forth in the following Table Three, as well as the measured initial viscosity, viscosity after three days, SAFT, and low temperature adhesion test results.

TABLE THREE

	HMA-1	HMA-2	HMA-3	HMA-4	HMA-5	HMA-6	HMA-7	HMA-8	HMA-9
Polymer A (density = 0.875 g/cm ³ ; I ₂ = 246 g/10 min.)	100	100	100	0	0	0	0	100	100
Polymer B (density = 0.897 g/cm ³ ; melt viscosity at 177°C = 5200 centipoise)	0	0	100	100	100	100	100	0	0
Polymer C (density = 0.870 g/cm ³ ; melt viscosity at 177°C = 355 centipoise)	200	200	0	300	200	0	0	0	0
Wax 1 (density = 0.968 g/cm ³ ; melt viscosity at 177°C = 395 centipoise)	0	0	0	0	0	30	30	0	0
Polywax™ 2000 Wax	33	33	22	0	0	0	0	0	0
CP Hall 1246 Paraffinic Wax	0	0	0	0	0	0	0	40	60
Escorez™ E1310LC Tackifier	33	66	22	0	100	40	0	0	0
Foral™ 105 Tackifier	0	0	0	0	0	0	40	0	0
Piccotac™ 115 Tackifier	0	0	0	0	0	0	0	40	60
Irganox™ 1010 Antioxidant	0	0	0	0	0	0.25	0.25	0.25	0.25
Initial viscosity (cPs)	2600	1570	1310	745	570	2020	2080	5700	2710
Viscosity after 3 days (cPs)	2440	1600	2200	2000	545	1900	1935	6050	3300
SAFT (°F (°C))			184 (84)	190 (87.8)			230 (110)		
Low temperature adhesion *	PT	PT	PT	PT	PT				

* PT indicates paper tear occurred.

Examples 10-15: HMA's not Incorporating Tackifier

The following formulations are prepared at a polymer:wax ratio of 90:10 by weight. Polymer F was prepared as set forth above. The polymers employed in HMA-10, HMA-11, HMA-12, and HMA-13 were substantially linear ethylene/1-octene copolymers prepared in accordance with the procedures of U.S. Patent No. 5,272,236. The wax used was Polywax™ 2000 ethylene homopolymer, available from Petrolite, Inc.

The samples were prepared by melting the components on a hot plate with stirring until a uniform mixture was obtained. The samples were allowed to cool.

Three small pieces of the polymer/wax samples were placed approximately 3/8 inch (1 cm) apart on the fiber side of a given paper board. The other piece of paperboard, coated side to sample, was placed on top. The structure was placed in a press, maintained at 180°C for 15 seconds with approximately 500 psi (3.4 MPa) pressure, and was then removed and cooled. The HMA/paperboard structures were tested for paper tear .

A description of the HMA compositions, as well as the results of the paper tear test are set forth in Table Four.

TABLE FOUR

	HMA-10	HMA-11	HMA-12	HMA-13	HMA-14	HMA-15
Polymer density (g/cm ³)	0.87	0.87	0.872	0.86	0.867	0.866
Polymer melt index (I ₂ (g/10 min.))	1	30	70	70	842	981
Weight percent polymer	90	90	90	90	90	90
Weight percent wax	10	10	10	10	10	10
Paper-to-clay adhesion--Weyerhaeuser board*	No	No	Yes	Yes	Yes	Yes
Paper-to-clay adhesion--SARAN box (Cascade Industries, Canada)*	No	No	Yes	Yes	Yes	Yes
Paper-to-clay adhesion Mead paperboard*	No	No	Yes	Yes	Yes	Yes

* A "yes" result means that paper tear was observed upon separating the paperboard/HMA/paperboard laminate; a "no" result means that no paper tear was observed upon separation.

Examples 16-24: Evaluation of HMA's for SAFT

The formulations set forth in Table Five were prepared, with Polymers A, B, D, and E, and Waxes 2, 3, and 4 being prepared by the procedures set forth above. The resultant hot melt adhesives were applied to 20 point paperboard boxes such as are employed in the packaging of rolls of food packaging film, for example SARAN-
5 WRAP™ (trademark of The Dow Chemical Company), and to a cardboard such as is employed in cartons for packaging the 20 point paperboard boxes in case-size quantities.

The formulations, as well as representative properties thereof, are set forth in
10 Table Five.

TABLE FIVE

	HMA-16	HMA-17	HMA-18	HMA-19	HMA-20	HMA-21	HMA-22	HMA-23	HMA-24
Polymer A (density = 0.875 g/cm ³ ; I ₂ = 246 g/10 min.)	100.0	0	0	0	0	0	0	0	0
Polymer B (density = 0.897 g/cm ³ ; melt viscosity at 177°C = 5200 centipoise)	0	100.0	0					0	
Polymer D (density = 0.883 g/cm ³ ; melt viscosity at 177°C = 5000 centipoise)	0	0	100.0	0	0	0	0	0	0
Polymer E (density = 0.893 g/cm ³ ; melt viscosity at 177°C = 12,500 centipoise)	0	0	0	0	0	0	0	100.0	0
Polymer F (density = 0.893 g/cm ³ ; melt viscosity at 177°C = 4000 centipoise)	0	0	0	100.0	100.0	100.0	100.0	0	100.0
Polywax™ 2000 Wax	115.0	0	0	0	0	0	0	0	0
CP Hall 1245 Paraffinic Wax	0	0	0	20.0	20.0	0	0	0	0
Wax 2 (density = 0.948 g/cm ³ ; melt viscosity at 177°C = 350 centipoise)	0	40.0	0		0	0	0	0	0
Wax 3 (density = 0.960 g/cm ³ ; melt viscosity at 177°C = 512 centipoise)	0	0	60.0	0	0	0	0	0	0

(Continued on the next page).

Wax 4 (density = 0.937 g/cm ³ ; melt viscosity at 177°C= 400 centipoise)	0	0	0	40.0	40.0	100.0	80.0	80.0	80.0
Escorex™ E1310 Tackifier	115.0	0	0	0	0	0	0	0	0
Foral™ 105 Tackifier	0	40.0	40.0	40.0	40.0	80.0	0	0	0
Piccotac™ 115	0	0	0	0	0	0	50.0	50.0	50.0
Kaydol™ Mineral Oil	0	0	0	0	10.0	0	0	0	20.0
Irganox™ 1010 antioxidant	0.7	0.4	0.4	0.4	0.4	0.6	0.5	0.5	0.5
100g SAFT 20pt paperboard (°C)	120	125	120	95	105	110	110	110	110
100g SAFT cardboard (°C)	120	130	120	105	105	110	110	110	110
Close time (seconds)	< 5	< 5	< 5	< 5	< 10	< 5	< 5	< 5	< 5
Open time (seconds)	25	20	25	30	25	35	25	20	30
Viscosity of Hot Melt Adhesive 177°C (centipoise)	1030	1940	1422	1037	758	865	1275	2740	942
Viscosity of Hot Melt Adhesive after 3 days (centipoise)	995	1895	1467	920	N/D	800	N/D	2850	930

N/D = not determined

Hot Melt Adhesive Formulations for Bonding Polyolefins

The hot melt adhesive formulation HMA-22, described in Table Five, was used to demonstrate the ability of the hot melt adhesives of the invention in the bonding of polyolefin substrates. Several 6 inch (15.2 cm) by 1 inch (2.5 cm) by 0.115 inch (0.292 cm) test coupons were cut from compression molded plaques of substantially linear ethylene/1-octene interpolymers available from The Dow Chemical Company as Affinity SM 1300 (having a density of 0.902 g/cm³ and a melt index (I₂) of 30 g/10 minutes) and Affinity SM-8400 (having a density of 0.870 g/cm³ and a melt index (I₂) of 30 g/10 minutes).

In the first experiment, the surface of the coupons of Affinity SM 1300 was heated to 80°C, and the surface of the coupons of the Affinity SM 8400 was heated to 60°C by heating in convection ovens for 20 minutes, or until the specimens were brought into thermal equilibrium with the oven environment. Likewise, HMA-22 was melted and stabilized to 392°F (200°C) in a hot glue gun. The HMA-22 was quickly dispensed onto the surface of the preheated coupons. One of each type of coupon was pressed together by applying light finger pressure, and were immediately further pressed by application of 5 pounds (2.2 kg) force using a 5 pound (2.2 kg) roller. The composites were allowed to cool to room temperature.

In the second experiment, the first experiment was repeated, except that the coupons were not preheated, and the like, the hot melt adhesive HMA-22 was dispensed at 392°F (200°C) onto coupons which were maintained at room temperature.

The bonded coupons were tested by peeling by hand. The specimens of the first experiment exhibited very good adhesion. In all cases, the samples failed by the Affinity SM 8400 layer failing in the tensile mode. The specimens of the second experiment showed a mixed mode of adhesion, as both adhesive and cohesive failures were present at the same time on most test coupons. The results were verified by performing T-peel testing on remaining test coupons. The bonded coupons of the first experiment exhibited an average T-peel strength of 21.4 ± 2.2 pounds/linear inch (24.7 ± 2.5 kg/cm). The bonded coupons of the second experiment exhibited an average T-peel strength of 14.7 ± 0.9 pounds/linear inch (17.0 ± 1 kg/cm).

Hot Melt Adhesive Formulations of Ethylene/ α -olefins with Ethylene Acrylic Acid and Ethylene Vinyl Acetate

The polymers, tackifier, wax, and antioxidant were simultaneously added in the indicated amounts to a Haake Rheocord 40 mixer using a 200 g mixing bowl
5 maintained at about 130°C at 95 revolutions per minute. The ingredients were mixed for about 5 minutes, until they became molten.

Ethylene acrylic acid (EAA) 5990 is commercially available from The Dow Chemical Company. Ethylene vinyl acetate (EVA -Elvax 210; 28 percent VA, 200 g/10 min. melt index) is commercially available from E. I. duPont de Nemours
10 Company. Viscosity, viscosity after 3 days, open and close times, 500 gram SAFT, 100 gram SAFT, 100 gram PAFT and low temperature mandrel tests were performed as set forth above.

Sample HMA 25 is formulated from 100.0 phr of a homogeneous ethylene/1-octene interpolymer having a density of 0.890 g/cc and a melt viscosity at 350°F
15 (177°C) of 5000 centipoise, 30.0 phr of a homogeneous ethylene homopolymer having a density of 0.960 g/cc and a melt viscosity at 350°F (177°C) of 300 centipoise, 40.0 phr of Foral™ 105 tackifier, 0.3 phr of Irganox™ 1010 antioxidant, and 18.9 phr Primacor™ 5990 ethylene acrylic acid copolymer. The formulation has a melt viscosity at 350°F (177°C) of 2775 centipoise, a close time of 5 seconds, an open time
20 of 10 seconds, a 100 gram SAFT of 100°C, a 500 gram SAFT of 115°C, a PAFT of 115°C, and a low temperature mandrel test which indicates 1/4 partial paper fail of Container Corporation of America.

Sample HMA 26 is formulated from 100.0 phr of a homogeneous ethylene/1-octene interpolymer having a density of 0.890 g/cc and a melt viscosity at 350°F
25 (177°C) of 5000 centipoise, 30.0 phr of a homogeneous ethylene homopolymer having a density of 0.960 g/cc and a melt viscosity at 350°F (177°C) of 300 centipoise, 40.0 phr of Foral™ 105 tackifier, 0.3 phr of Irganox™ 1010 antioxidant, and 18.9 phr Elvax™ 210 EVA. The formulation has a melt viscosity at 350°F (177°C) of 3075 centipoise, a close time of 5 seconds, an open time of 10 seconds, a 100 gram SAFT of
30 100°C, a 500 gram SAFT of 120°C, a PAFT of 125°C, and a low temperature mandrel test which indicates 1/4 partial paper fail of Container Corporation of America.

II. Hot Melt Pressure Sensitive Adhesive Examples

Preparation of Adhesive Formulations

5 The indicated polymer, tackifier, plasticizer, and antioxidant were simultaneously added in the indicated amounts to a Haake Rheocord 40 mixer using a 200 gram mixing bowl maintained at about 130°C at 95 revolutions per minute. The ingredients were mixed for about 5 minutes, until they became molten.

 Escorez™ 5300 petroleum hydrocarbon resin is a tackifier available from
10 Exxon Chemical Company (Houston, TX). Escorez™ 5300 has a density of 1.09 g/cm³, a weight average molecular weight of 354, a number average molecular weight of 354, and an M_w/M_n of 1.43.

 Irganox™ B900 hindered phenolic antioxidant is available from Ciba-Geigy.

 Irganox™ 1010 hindered phenolic antioxidant is available from Ciba-Geigy.

15 Polyisobutylene is available from Amoco.

 Examples PSA-27 through PSA-32 were tested for initial viscosity and viscosity after three days, using a Brookfield viscometer at 350°F, probe tack, modulus (G'), and peak tan delta. The formulations and the measured properties are set forth in Table Six. Note that in the case of modulus and peak tan delta, the reported values
20 were extracted from a computer-generated plot of the results.

 As illustrated in Table Six, the adhesives of Examples 27, 29, 30, 31 and 32 meet the Dahlquist criteria, indicating their suitability as a traditional PSA, with Examples 27, 29, 30, and 31 further meeting the criteria that the glass transition temperature range from -20 to 20°C. Examples 27 and 28 illustrate the trend that as
25 number average molecular weight decreases, storage modulus likewise decreases. Example 29 illustrates the use of added tackifier to increase the glass transition temperature of the formulation.

 Dual molecular weight blends appear to offer a unique balance of properties which are not in accordance with the law of mixtures. In particular, while the blend of
30 Example 31 has a storage modulus (G') at 25°C which is intermediate that of

Examples 27 and 28, the probe tack of Example 31 exceeded that of Example 28, indicating that the blends of the invention offer a synergistic behavior.

As further illustrated in Table Six, Example 27 may be employed as a cold temperature label or a PSA tape, Example 24 may be employed as a PSA tape,

- 5 Example 30 may be employed as a low peel label or a freezer label; Example 31 may be employed in high peel labels or disposables applications; Example 32 may be employed in PSA tape.

TABLE SIX

	PSA-27	PSA-28	PSA-29	PSA-30	PSA-31	PSA-32
Polymer G (density = 0.867 g/cm ³ ; I ₂ = 842 g/10 min.)	0	100/45.2	0	0	50/22.6	0
Substantially linear ethylene/1-octene interpolymers (density = 0.864 g/cm ³ ; I ₂ = 13 g/10 min.)	100/45.2	0	100/36.9	0	50/22.6	0
Affinity™ EG 8200 (0.870 g/cm ³ ; I ₂ = 5 g/10 min.)	0	0	0	100/41.5	0	0
Affinity™ EG 8180 (0.863 g/cm ³ ; I ₂ = 0.5 g/10 min.)						50/22.7
Substantially linear ethylene/1-octene interpolymers (0.885 g/cm ³ ; I ₂ = g/10 min.)						50/22.7
Escorez™ 5300 (Exxon)	100/45.2	100/45.2	150/55.4	0	100/45.2	0
Indopol™ (Amoco)	0	0	0	125/51.9	0	100/45.5
Drakeol™ 34 (Premcor)	20/9.0	20/9.0	20/7.4	0	20/9.0	20/9.1
Duoprime™ 200 (Lyondell)	0	0	0	15/6.2	0	0
Irganox™ B900 (Ciba Geigy)	1/0.5	1/0.5	1/0.4	0	1/0.5	0
Irganox™ 1010 Antioxidant	0	0	0	1/0.4	0	0
Viscosity at 350° (cPs)						
Probe tack (g)	50	329	153	129	552	0
G' at 0°C (dynes/cm ² (Mpa))	1.26 x 10 ⁷ (1.26 MPa)	1.26 x 10 ⁵ (0.126 MPa)	3.98 x 10 ⁷ (3.98 MPa)	1.78 x 10 ⁶ (0.178 MPa)	5.62 x 10 ⁶ (0.562 MPa)	5.01 x 10 ⁷ (5.01 MPa)
G' at 25° C (dynes/cm ²)	2.00 x 10 ⁶ (0.200 MPa)	3.98 x 10 ⁴ (0.00398 MPa)	1.41 x 10 ⁶ (0.141 MPa)	5.62 x 10 ⁵ (0.0562 MPa)	7.08 x 10 ⁵ (0.0708 MPa)	5.89 x 10 ⁶ (0.589 MPa)
G' at 50°C (dynes/cm ²)	3.16 x 10 ⁵ ((0.0316 MPa)	NA	1.78 x 10 ⁵ (0.0178 MPa)	1.58 x 10 ⁵ (0.0158 MPa)	3.16 x 10 ⁴ (0.00316 MPa)	2.24 x 10 ⁶ (0.224 MPa)
G' at 75°C (dynes/cm ²)	2.00 x 10 ⁵ (2.00 kPa)	NA	1.58 x 10 ⁴ (1.58 kPa)	7.08 x 10 ³ (0.708 kPa)	3.98 x 10 ³ (0.398 kPa)	2.51 x 10 ⁵ (25.1 kPa)
Temp. at which G' = 10 ⁶ dynes/cm ² (10 kPa) (°C)	90	32	79	74	57	90
Temp. at which G' = 10 ⁵ dynes/cm ² (100 kPa) (°C)	59	21	55	55	43	147
Peak tan delta (°C)	-12	-21	0	-55	17	0

Likewise, pressure sensitive adhesives may be prepared using a substantially linear ethylene polymer in combination with tackifier and a high density polyethylene having a lower molecular weight as indicated by a melt index (I_2) of 25 g/10 min. As set forth in the following Table Seven, such pressure sensitive adhesives exhibit probe tack values comparable to the adhesive used on Scotch™ magic tape (368 g).

TABLE SEVEN

	PSA-33	PSA-34
Substantially linear ethylene/1-octene interpolmer (density = 0.855 g/cm ³ ; I_2 = 1 g/10 min)	17.4 percent	17.4 percent
HDPE 2455 (density = 0.955 g/cm ³ , I_2 = 25 g/10 min)	7.5 percent	
Affinity™ SM 1300 (density = 0.902 g/cm ³ ; I_2 = 30 g/10 min)		7.5 percent
Escorez™ 1310LC (Exxon)	54.9 percent	54/9 percent
Kaydol™ (Witco)	20.7	20.7
Irganox™ 1010 Antioxidant	0.25	0.25
Viscosity at 350°F (177°C) (cPs)	42,000	24,650
Probe tack (g)	537	264

10

III. Application Specific Adhesive Examples

The following examples were made using a sigma blade mixer or a vertical upright mixer with standard hot melt blending techniques and tested in accordance with the test methods described above. Unless indicated otherwise, the homogeneous ethylene/ α -olefin interpolymers utilized in the examples are depicted in the following Table Eight. The presentation of the examples in this manner is a matter of convenience and is in no way intended to be limiting. Adhesive examples targeted for specific end-use applications also have utility for other applications.

15

TABLE EIGHT

Supplier	Designation	Melt Index (I ₂ in g/10 min)	Density (g/cm ³)	Comonomer
Exxon	Exxpol SLP-0380	20	0.865	Propylene
Exxon	Exxpol SLP-0394	5	0.865	Propylene
Exxon	Exxpol SLP-0397	120	0.885	Propylene
Exxon	Exxpol SLP-0527	125	.901	Butene
Exxon	Exxpol SLP-0592 Exact 5008	10	0.865	Butene
Exxon	Exxpol SLP-0599	20	0.865	Butene
Exxon	Exxpol SLP-0173	3.5	.910	Hexene
Exxon	Exxpol SLP-0728 Exact 3031	3.5	.900	Hexene
Dow	SM-1300	30	.902	Octene
Dow	SM-8400	30	.870	Octene
Dow	EG-8150	0.5	.870	Octene
Dow	EG-8200	5	.870	Octene
Dow	EG-8100	1	.870	Octene
Dow	SM1250	30	.885	Octene
Dow	DPF 1150-01	0.9	.901	Octene
Dow	*EIP 4	28	.868	Octene
Dow	EIP 5	1	.858	Octene
Dow	EIP 6	30	.855	Octene
Dow	EIP 7	200	.870	Octene
Dow	EIP 8	100	.900	Octene
Dow	EIP 9	100	.855	Octene
Dow	EIP 10	** 5000 cps	.870	Octene
Dow	EIP 11	** 5000 cps	.890	Octene
Dow	LDPE 959S	60	.920	Octene

EIP - Experimental Substantially Linear Ethylene/1-Octene Interpolymer; *In-reactor
5 mixture; ** Brookfield Viscosity (MI not measurable)

Table Eight A: Other Ingredients

Tradename	Description	Supplier
Tackifying Resins		
Escorez 2520	C ₉ /C ₉ hydrocarbon blend	Exxon
Escorez 5400 (ECR-177)	hydrogenated dicyclopentadiene	Exxon
Escorez 2520	C ₉ /C ₉ hydrocarbon blend	Exxon
Escorez 2520	C ₉ hydrocarbon	Exxon
Eastotac H-100	hydrogenated C ₉	Eastman
Eastotac H-130	hydrogenated C ₉	Eastman
Sylvatac 1103	rosin ester	Arizona
Plasticizers		
	*500 naphthenic oil	Penzoil
	*1200 naphthenic oil	Penzoil
Kaydol	white mineral oil	Witco
Parapol 1300	1300 M _w polybutene	Exxon
Benzoflex 352	1,4 cyclohexane dimethanol dibenzoate	Velsicol
Waxes		
Victory® Amber Wax	* 160°F Microwax	Petrolite
Castorwax	hydrogenated castor oil	Caschem
Okerin® 236 TP	parafin 155°F	Astor Wax
Parafint H4(*HMP Wax)	225°F Fischer Tropisch	Moore & Munger
Besquare® 195	195°F Microwax	Petrolite
Bareco PX-100	225°F Fischer Tropisch	Bareco
Modifying Polymers		
Kraton® G-1657	13 percent styrene, 35 percent diblock styrene-ethylene-butylene-styrene block copolymer	Shell
Elvax 260	28 percent vinyl acetate, 5 melt index	Dupont
Elvax 150	33 percent vinyl acetate, 44 melt index	Dupont
Elvax 410	18 percent vinyl acetate, 500 melt index	Dupont
	*EnBA 35 percent BA, 320 melt index	
HL-2660	Polyamide	H.B. Fuller Co.
HL-6088	Polyamide	H.B. Fuller Co.
Petrothene NA 601	.903 g/cm ³ , 2000 melt index low density polyethylene	Petrolite
Epolene C-15	.906 g/cm ³ , 4200 melt index polyethylene	Eastman
Irganox 1010	hindered phenol antioxidant	Ciba-Giegy

* Description rather than tradename indicated in the examples.

Nonwoven Construction Adhesives

Adhesives of the invention for use as nonwoven construction adhesives are set forth below in Tables Nine and Nine A.

5 Examples 35-57 of Table Nine represents nonwoven construction adhesives useful for the assembly of various disposable articles such as disposable diapers, sanitary napkins, surgical gowns, and the like wherein a body fluid impermeable backsheet is typically bonded to a nonwoven substrate. The disposable article of the present invention comprises at least two layers wherein at least one of said layers is a
10 body fluid impermeable barrier and at least one of said second layers is a body fluid permeable cover; wherein at least one layer is attached to at least one other layer by the adhesive composition of the present invention. The disposable article may also optionally contain at least one layer or material selected from the group consisting of absorbents, tissues, elastomeric materials, superabsorbent polymers, and combinations
15 thereof. The body fluid cover is typically a polyolefin film, such as polyethylene, polypropylene, ethylene-vinyl acetate, and especially a homogeneous ethylene/ α -olefin interpolymer film, provided as a roll good. Alternatively, the barrier layer can be made in-line by coating a thermoplastic composition to a carrier material such as a nonwoven. In-line film forming is of particular interest for materials which are
20 unsuitable, due to tack, undesirable rheological properties, or any other constraint which renders the material undesirable for making prefinished roll goods. Preferably, in-line barriers are made using a noncontact slot coat application method described in detail in H.B. Fuller's copending PCT application, Application No. EP 96/00377 filed January 30, 1996.

25 The majority of the adhesives examples are pressure sensitive in nature. However, some of the examples, particularly those comprising Benzoflex 352 or alternatively relatively high concentrations of the homogeneous ethylene/ α -olefin interpolymer, and the like, greater than about 40 weight percent of the homogeneous ethylene/ α -olefin interpolymer, are relatively tack-free upon cooling. Examples NW-
30 44 and NW-45 are substantially tack-free upon cooling and are intended for nonwoven to nonwoven bonding. The bonds were made and evaluated in accordance with the

previously mentioned "Fineline and Spray" test method. The application conditions and resulting peel results are recorded in Table Ten.

Surprisingly, as illustrated in Table Ten, these adhesive compositions have excellent spray properties and spray bond strengths, even though the viscosity at application temperature is significantly higher than a typical block copolymer based adhesive composition, such as HL-1280 (H.B. Fuller), an industry standard nonwoven construction adhesive for bonding polyolefin films. Although nonwoven construction adhesives are exemplified, the adhesives of the present invention are also surmised to be suitable for elastic attachment, frontal tape, as well as multipurpose nonwoven applications.

Polyolefin films comprising homogeneous ethylene/ α -olefin interpolymers are becoming increasingly popular due to their reduced stiffness and improved tactile quality in comparison with conventional polyethylene films. The adhesives of the present invention are expected to exhibit even higher bond strength on films comprising homogeneous ethylene/ α -olefin interpolymers.

Table Nine: Nonwoven Construction Adhesives

Ingredient	4156-77-1 NW-35	4156-80-1 NW-36	4156-78-1 NW-37	5179-10-1 NW-38	5402-42-1 NW-39	5402-4-1 NW-40	HL-1624 NW-41	HL-1617 NW-42*	HL-1625 NW-43*	NW-44	NW-45	5338-57-2 NW-46
SLP-0592	25.0		25.0									
SLP-0599	25.0											
EIP 6				17								
DPF-1150.01				3								
XUR 5990100					22							20
EIP 4												
EIP 7						40						
EG 8200							16	12	12			
0.87 g/cm ³ /2200 MI**										50		
0.86 g/cm ³ /200 MI**											70	
Escorez 2520 (Exxon)	25.0	25.0										
Excurez 5320 (Exxon)					55							55
Escorez 5400 (Exxon)	49.0	49.0	49.0	55		50	55	56.8		50	30	
Escorez 2596									56.8			
500 Naphthenic Oil Kaydol					23	10	27	28	28			
Benzoflex 352 (Velsicol)			25.0	25								25
Irganox 1010	1.0	1.0	1.0				.2	.2	.2			
Viscosity @ 250°F (cps)	150,000	78,000	110,000					8,175	8,400			
@ 275°F (cps)	81,000	42,000	65,000				13,900	4,375	4,640			
@ 300°F (cps)	48,000	24,500	40,000	7650			8,000	2,600	2,740			
@ 325°F (cps)	29,500	15,000	25,000	5000	8425	3733	4,890	1,996	1,710			4395
@ 350°F (cps)	19,000	9,375	17,500				3,095		1,135			

** Substantially linear ethylene/1-octene interpolymers available from The Dow Chemical Company; All amounts are in pph; Examples indicated by * further contain 2 weight percent Parafint C-80

Table Nine-A

Reference #	NW-47	5179-22-2 NW-48	5338-53-1 NW-49	5402-18-2 NW-50	5336-53-2 NW-51	Comparative Example B
EIP 5		10	6	14		
DPF 1150.01			6			
EIP 4						
Rextac 2385 (Rexene)					25	
EIP 10	30					25
EIP 11	30			6		
ECR 177		65	60	62	55	
Escotez 5320	40			18		
Kaydol		25	23		20	55
Visc @ 300F	4300					20*
Visc @ 325F		3250	5500	20500	8813	1025

All amounts are as weight percent.

Comparative Example B indicated by * utilizes 500 Napthenic Oil in place of Kaydol oil

TABLE TEN: Nonwoven Construction Bonding Results

Example	Adhesive Temperature (°F (°C))	Air Pressure (psi (MPa))	Spiral Spray Peel (g/lineal in. (g/cm))	Fineline Peel (g/cm)	Comments
NW-35	350 (177)	30 (0.21)	210 (40)	340 (160)	Destructive Bonds
NW-36	300 (149)	26 (0.18)	190 (20)	211 (40)	Destructive Bonds
NW-38*	275 (135)		126 (12)	55 (5)	Cohesive Failure, Low Application Temperature
NW-39	325 (163)	28 (0.19)	162 (19)	203 (27)	Destructive Bonds
NW-40	300-325 (149-163)		116 (19)	64 (7)	
NW-41	275-300 (135-149)	15 (0.10)	140 (55)	125	
NW-42	275 (135)	6 (0.041)	125 (49)	115	
NW-43	300 (149)	7 (0.048)	125 (49)	115	
NW-44	300 (149)	7 (0.048)	79 (9)	123 (15)	
NW-45	not tested				
NW-46	325 (163)	15 (0.10)	142 (18)	125 (18)	
NW-47	300 (149)	12 (0.083)	31 (7)	82 (21)	
NW-48	300-325 (149-163)		107 (14)	59 (10)	Very Soft
NW-49	300 (149)		151 (36)	103 (17)	
NW-50	325 (163)	15 (0.10)	184 (32)	235 (76)	Destructive Bonds
NW-51	325 (163)		129 (21)	160 (51)	
Comparative B	300 (163)		35 (20)	6 (3)	
Comparative A-FL-1280	275 (135)	15 (0.10)	95 (** (37))	175 (** (69))	(** running average)

* NW-37 not tested

Thermal Stability Testing

The pressure sensitive adhesives of Examples NW-41 through NW-45 were tested for thermal stability. The results are set forth in the following Table Eleven. As is exemplified by these thermal stability results, the adhesives of the present invention exhibit tremendously improved viscosity stability relative to block copolymer based adhesive compositions.

Table Eleven: Thermal Stability Testing (Brookfield viscosity at 300°F (149°C) (cps))

Viscosity	0	24 hrs	48 hrs	72 hrs	96 hrs	200 hrs	Delta 96	Delta 200
HL1280	2645	2425	2310	2065	1990	--	-25	--
(HL-1624) NW-41	9950	9900	9825	10200	10350	10450	4.0	5.0
(HL-1617) NW-42	2735	2540	2515	2650	2560	2750	-6.4	0.5
(5576-3-3) NW-43	9575	9550	9525	9475	9800	9400	2.3	-1.8
(HL-1625) NW-44	2300	2320	2130	2450	2440	2385	6.1	3.7

10

Positioning Adhesive

Positioning adhesives are typically pressure sensitive in nature and is sandwiched between the garment facing surface of a feminine napkin and release paper. Upon use the release paper is removed and the napkin is secured to an undergarment by means of the positioning adhesive. The current state of the art with respect to positioning adhesives can be found in U.S. Patent Nos. 4,136,699, 5,149,741 and 4,704,110. Pressure sensitive adhesives for use as positioning adhesives, as well as representative performance attributes thereof, are set forth in the following Table Twelve.

Table Twelve: Positioning Adhesives

	52	53	54
SLP-0592	25.0	20.0	20.0
SLP-0597	49.0	5.0	5.0
Eastotac H-130	49.0	49.0	---
ECR-177	---	---	49.0
Kaydol Oil	25.0	25.0	25.0
Irganox 1010	1.0	1.0	1.0
Initial T-Peel to Cotton (1 mil)	365g (5)	298g (16)	172g (23)
Initial T-Peel to Cotton (2 mil)	478g (19)	406g (13)	216g (26)

(95 percent Confidence Intervals)

5

Additional PSA Applications

The adhesives of the invention may be utilized as adhesives for use in industries other than nonwoven and personal care items. For instance, Examples 55 - 58 represent packaging PSA formulations for bonding rigid polyolefin containers (lunch meat containers) and for bottle labeling applications. Examples 55-56 demonstrate the utility of employing block copolymers, particularly in small concentrations, in combination with the essential homogeneous ethylene/ α -olefin interpolymer.

Example 59 represents an example of a "foam in place" gasket wherein the compositions serves a multipurpose of bonding, sealing, and gasketing.

Examples 60 and 61 represent rodent trap adhesives which are a substantial cost savings relative to existing technology. Typically, block copolymer-based adhesives for this application comprise from about 5 to about 20 percent by weight of the block copolymer. The adhesive composition covers the bottom surface of a container such as box and is subsequently baited to form a trap. Often an additive is incorporated directly into the adhesive which attracts rodents and eliminates the need for consumer-provided bait. The adhesive exhibits high tack and cohesive strength to restrain the rodent.

The various additional PSA examples, and representative performance attributes thereof, are set forth in the following Table Thirteen:

25

Table Thirteen: Additional Pressure Sensitive Adhesive Examples

Reference # Ingredient Trade name	(4230-44-1) Example 55	(4230-40-1) Example 56	(4230-39-1) Example 57	(4230-39-2) Example 58	(4156-80-2) Example 59	(4231-1-1) Example 60	(4231-1-2) Example 61
SLP-0592	9.0	11.7	15.0	14.6			10.0
SLP-0599					30.0	10.0	
Kraton™	6.0	2.9					
G-1657 (Shell)							
Eastotac™ H-100 (Eastman)	42.5	41.5	42.5	41.5			
ECR-177 (Exxon)						44.0	
Scorez™ 1310 (Exxon)							44.0
500 Oil (Naphthenic)	37.5	39.0	40.0	39.0			
1200 Oil (Naphthenic)						45.0	45.0
Kaydol Oil					40.0		
Micro wax 160	5.0	4.9					
Castor Wax			2.5	4.9			
Parafin 155					30.0		
Irganox 1010							
Viscosity @ 250°F (121°C)		6275 cps				1.0	1.0
@ 275°F (135°C)		3810					
@ 300°F (149°C)		2415					
@ 325°F (163°C)		1600					
@ 350°F (177°C)		1112					

All percentages are by weight percent

Adhesive Formulations Comprising Homogeneous Ethylene/ α -olefin Interpolymers and EVA:

The adhesives of the invention may further include, in addition to the homogeneous ethylene/ α -olefin interpolymers, one or more ethylene vinyl acetate copolymers. In particular, given the compatibility of homogeneous ethylene/ α -olefin interpolymers with EVA, adhesives comprising such a combination of polymers will find utility in, for instance, bookbinding applications as well as others where it is necessary for the hot melt adhesive to lose surface tack quickly after application to insure that the adhesive does not build up on the trimmer knives. Also, this compatibility facilitates the need to adjust the set time to accommodate various application equipment. Representative of such hot melt adhesive formulation comprising EVA which has from 18 to 33 weight percent vinyl acetate content, as well as representative performance attributes thereof, are set forth in the following Table Fourteen:

Table Fourteen: Adhesives Comprising Homogeneous Ethylene/ α -olefin Interpolymers and EVA

Reference #	4036-41-1	4036-41-2	4036-41-3	4036-41-4	4036-41-5	4036-41-6	4036-41-7
Trade Name	Example 62	Example 63	Example 64	Example 65	Example 66	Example 67	Example 68
Ingredient	40.0	40.0	40.0	40.0	30.0	30.0	30.0
SLP-0380							
Eastotac							
H-100	39.5	39.5	39.5	39.52	59.5	59.5	59.5
Parafin 155	20.0						
Irganox 1010	.5	.5	.5	.5	.5	.5	.5
Elvax 260 (28 percent vinyl acetate)		20.0			10.0		
Exvax 150 (33 percent vinyl acetate)				20.0		10.0	
Elvax 410 (18 percent vinyl acetate)			20.0				10.0

All amounts are in weight percent.

Bookbinding Adhesives

Certain of the claimed adhesives will find particular utility in the graphic arts industry as bookbinding adhesives. The target property ranges set forth in the following Table Fifteen can be achieved with the adhesives of the invention.

5

Table Fifteen: Target Bookbinding Properties

	Viscosity at 350°F	100 g Peel	Cold Crack	Ambient Range*	Tensile
Useful	≤ 10,000 cps	≥ 120°F (49°C)	≤ 40°F (4.4°C)	≥ 80°F (27°C)	≥ 350 psi (2.4 MPa)
Good	< 8,000 cps	> 130°F (54°C)	< 30°F (-1°C)	> 100°F (38°C)	> 500 psi (3.4 MPa)
Excellent	< 6,000 cps	> 140°F (60°C)	< 20°F (-7°C)	> 120°F (49°C)	> 600 psi (4.1 MPa)

*The ambient ranges is defined as the difference between the 100 g peel and the cold crack.

10

Representative bookbinding adhesives and representative performance attributes thereof are set forth in the following Tables Sixteen A and B.

As exemplified in Tables Sixteen A and B, for bookbinding applications it is preferred to employ a homogeneous ethylene/ α -olefin interpolymers having a density of 0.870 g/cm³ or less and a relatively low melt index, for example ranging from 10 to 20 g/10 min., at concentrations of 30 weight percent or less. To reduce the viscosity of the adhesive composition it is preferable to blend a second homogeneous ethylene/ α -olefin interpolymers having a melt index ranging from 100 to 2000 g/10 min. in combination with the low melt index homogeneous ethylene/ α -olefin interpolymers. It is a surprising result that adhesives can be prepared with this low density homogeneous ethylene/ α -olefin interpolymers without sacrificing heat resistance. Microwaxes are preferred waxes for bookbinding applications, particularly when combined with polar tackifiers such as rosin esters, rosin acids, hydrogenated rosin esters, terpene resins, styrenated terpenes, terpene phenolics, and mixtures thereof.

25

Table Sixteen A: Bookbinding Adhesives

Ingredient	4036-43-1 Example 69	4036-43-2 Example 70	4036-49-1 Example 71	4036-49-2 Example 72	4036-49-3 Example 73	Example 74	Example 75	Example 76	Example 77
SLP-0380	40.0	35.0	40.0	20.0		15.0	15.0		
SLP-0397				20.0	40.0	20.0	20.0		
SLP-0527								25.0	20.0
SLP-0592								10.0	15.0
Eastotac									
H-100	39.5	39.5	34.5	34.5	34.5	44.5		44.5	44.5
Eastotac									
H-130							44.5		
HMP Wax									
(Fischer									
Tropsch,	20	25.0	12.5	12.5	12.5	20.0	20.0	20.0	20.0
225 mp)									
Irganox 1010	.5	.5	.5	.5	.5	.5	.5	.5	.5
Paraffin 155			12.5	12.5	12.5				
PAFT (°F	140 (60)	138 (59)	112 (44)	112 (44)	105 (41)	128 (53)	139 (59)	141 (61)	147 (64)
(°C)									
SAFT (°F)	193 (89)	194 (90)	173 (78)	173 (78)	174 (79)	192 (89)	191 (88)	199 (93)	197 (92)
Cold Crack	10 (-12)	20 (-7)	5 (-15)	15 (-9)	25 (-3.9)	20 (-7)	30 (-1)	45 (7.2)	30 (-1)
(°F)									
Ultimate				510 (3.4			526	697 (4.8	606 (4.1
Tensile (psi)				MPa)				MPa)	MPa)
Viscosity @									
350°F (177°C)	32,000	20,100	26,200	14,500	6,675	10,350	11,800	8562	12,875
(cps)									

All amounts are by weight percent.

Table Sixteen B: Bookbinding Adhesives

Ingredient	Example 78	Example 79	Example 80	Example 81	Example 82	Example 83	Example 84	Example 85
0.87 g/cm ³ / I ₂ = 10 g/10 min**	14							
0.864 g/cm ³ / I ₂ = 14 g/10 min**	14	22.5	25	25	25	25	25	20.5
0.873 g/cm ³ ; I ₂ = 2200 g/10 min**		10						
0.864 g/cm ³ ; Melt viscosity at 177°C = 10000 cps***			10	10	10	10	10	15
Parafint H4	25	25						11
Escorez 5400	46.5							21 + 21*
Eastatac								
H-100-R		42.5	39.5	29.5	24.5	20		
1950F Microwax			25	25	25	25	25	11
Nirez 2019				10	15	19.5	39.5	
Irganox 1010	.2	.5	.2	.2	.2	.2	.2	.5
Irganox 1076	.3		.3	.3	.3	.3	.3	
Cold Crack (°F (°C))	25 (-3.8)	10 (-12)	-5 (-21)	0 (-18)	5 (-15)	5 (-15)	5 (-15)	10 (-12)
Ambient Range (°F(°C))	115.6 (46)	132 (56)	138 (59)	139 (59)	132.5 (56)	128.5 (54)	127 (53)	128 (53)
100 g Peel (°F(°C))	140 (60)	142 (61)	133 (56)	139.2 (60)	137.5 (59)	133.8 (57)	132 (56)	138 (59)
Viscosity @ 350°F (177°C) (cps)	9250	4750	7215	7325	7825	7625	7440	5900
Ultimate Tensile (psi(Mpa))	591 (4.07)	561 (3.87)	369 (2.54)	403 (2.78)	408 (2.81)	429 (2.96)	542 (3.74)	366 (2.52)

* Escorez 5615

** Substantially linear ethylene/1-octene interpolymers; homogeneous ethylene/1-octene interpolymer (all available from The Dow Chemical Company)

All amounts are reported in weight percent.

Case and Carton Seal Adhesive

The hot melt adhesives of the invention will find particular utility as case and carton seal adhesives. Representative adhesives for case and carton sealing, and
5 representative performance attributes thereof, are set forth in the following Table Seventeen. Table Seventeen illustrates the utility of blending small concentrations of the homogeneous ethylene/ α -olefin interpolymer with a second polyethylene, resulting in improved cold temperature properties and heat resistance.

Table Seventeen: Case and Carton Seal Adhesives

	4056-43-1 Example 53	4056-46-1 Example 54	4056-60-1 Example 55	4056-65-1 Example 56	4056-65-2 Example 57	4056-65-3 Example 58	4056-65-4 Example 59	HL 7400
Eastotac H-100 (Eastman)	50	50	35	35	35	35	35	30
SLP-0599	12				10			
SM-8400			10					
SLP-0380				10				
SLP-0738						10		
Epolene C-15 (Eastman)	20	32	50	50	50	50	60	
Parafint H-4	18	18	5	5	5	5	5	
Petrothene NA601								70
Viscosity @ 350°F (177°C) (cPs)	1325	1800	2025	2900	2800	7600	730	2025
Bonding Testing Corrugated:								
Room Temp	1	4	1	1	1	1	1	1
40°F (4.4°C)	2	4	1	1	1	1	4	4
0°F (-18°C)	4	4	1	3	3	1	4	4
PAFT (°F (°C))	147 (64)	88 (31)	138 (59)	120 (49)	130 (54)	138 (59)	110 (43)	105 (41)
SAFT (°F (°C))	192 (89)	197 (92)	190 (88)	190 (88)	190 (88)	190 (88)	190 (88)	197 (92)

All amounts are reported in weight percent.

1 = Full Fiber Tear 2 = Shallow Fiber Tear 3 = Partial Fiber Tear 4 = No Fiber Tear
HL 7400, Commercial Case and Carton Seal (HB Fuller)

Packaging Adhesives

The hot melt adhesives of the invention will find utility in a variety of
5 packaging applications. Their success in such applications is attributable in part to the
fact that by employing the essential homogeneous ethylene/ α -olefin interpolymer, a
good balance of heat resistance (PAFT/SAFT) and cold temperature properties can be
achieved. The following Tables Eighteen A, B, and C report a variety of adhesive
10 compositions intended for various packaging applications, as well as various
performance attributes thereof.

As illustrated in Tables Eighteen A, B, and C, for high performance packaging
applications, the homogeneous ethylene/ α -olefin interpolymer employed will have a
density of 0.87 g/cm³ or less, and a melt index (I₂) of about 500 g/10 min. or less, and
will be employed at concentrations of about 30 to 45 weight percent. Preferably, the
15 homogeneous ethylene/ α -olefin interpolymer will be provided in combination with
from 25 to 45 weight percent of high melt point wax, and from 20 to 50 weight percent
of a high melt point resin. Example 101 demonstrates the compatibility of the
homogeneous ethylene/ α -olefin interpolymer with EnBA. This combination is
surmized to be useful for further improving the low temperature adhesion and thermal
20 stability as well as improve the compatibility with non-polar tackifying resins.

Table Eighteen A: Packaging Adhesives

	5342-56-1 Example 86	5342-56-2 Example 87	5342-56-3 Example 88	5342-56-4 Example 89	5342-56-5 Example 90	5342-60-1 Example 91	5342-60-2 Example 92	5342-60-3 Example 93
Dow SM-8400	20	20	22.5	22.5	18	20	20	18
Parafilm H-4	20	25	20	25	17	15	10	10
Eastotac H-100	60	55	57.5	52.5	65	65	70	72
Irganox 1010	.25	.25	.25	.25	.25	.25	.25	.25
Viscosity @ 350° F (177°C) (cPs)	151	1270	2280	1140	2315	1865	2705	-----
PAFT (°F (°C))	158.5 (70)	159 (71)	152 (67)	157.8 (70)	153.8 (68)	163 (73)	153.7 (68)	153 (67)
SAFT (°F (°C))	188.2 (87)	192.8 (89)	192.6 (89)	199.8 (93)	185.8 (85)	186.4 (86)	170.4 (77)	160.8 (72)
Bonding Testing*:								
70°F (21°C)	100 percent	100 percent	100 percent	100 percent	100 percent	100 percent	100 percent	100 percent
Clay Coat Surface	100 percent	100 percent	100 percent	100 percent	100 percent	100 percent	100 percent	100 percent
Uncoated Surface	85 percent	98 percent	98 percent	75 percent	100 percent	83 percent	80 percent	10 percent
30°F (-1°C)	100 percent	100 percent	100 percent	100 percent	100 percent	100 percent	100 percent	100 percent
Clay Coat Surface	100 percent	100 percent	100 percent	100 percent	100 percent	100 percent	100 percent	100 percent
Uncoated Surface	0 percent	100 percent	100 percent	15 percent	70 percent	50 percent	5 percent	0 percent

All amounts are reported in weight percent.

* Adhesion to MEAD Carrier-kote (high wet strength), Average of two bonds - percent fiber tear

Table Eighteen B- Packaging Adhesives

Reference #	5342-521 Ex. 94	5342-52-2 Ex. 95	5342-52-3 Ex. 96	5342-52-4 Ex. 97	5342-53-1 Ex. 98	5342-53-2 Ex. 99	5709-26-1 Ex. 100	5709-26-3 Ex. 101	5709-26-5 Ex. 102
Affinity™ SM-8400	25	28	30	35	30	35	10	10	10
0.87 g/cm ³ I ₂ = 200 g/10 min**							15		
EVA (18 percent VA, 400 MI)									15
EnBA (35 percent BA, 320 MI)								15	
Parafllint H4	20	25	20	20	25	25	25	25	25
Eastotac H-100-R	55	47	50	45	40-45	40	50	50	50
Irganox 1010	0.2	0.2	0.2	0.2	0.2	0.2	0.3	0.3	0.3
Visc. @350°F (177°C)	3680 cps	4370 cps	5220 cps	8680 cps	4480 cps	7700 cps	1250 cps	1030 cps	840 cps
Peel (°F)	158.5 ± 2.72	155.8 ± 5.1	160.2 ± 5.6	154.8 ± 3.3	156.5 ± 2.9	159.6 ± 5.2	151.6 ± 2.0	156.5 ± 2.9	148.8 ± 1.7
Shear (°F)	186.4 ± 2.99	194.4 ± 2.4	188.0 ± 1.76	189.2 ± 5.6	194.8 ± 2.2	193.8 ± 2.39	196.2 ± 1.6	194.8 ± 2.2	195 ± 2
Cloud Pt.(°C)	101	103	102	104	106	102	90	95	95
Open T.(°C)	75.5	76.1	71.5	78.2	78.1	77.3		78.1	77.3
Set temp (°C)	61.1	66.3	66.7	63.7	66.1	68.4		66.1	68.4
Bonding Test									
70°F (21°C)	95 percent FT	95 percent FT	100 percent FT	100 percent FT	98 percent FT	99 percent FT	100 percent FT*	100 percent FT*	100 percent FT*
30°F (-1°C)	40 percent FT	80 percent FT	75 percent FT	90 percent FT	85 percent FT	95 percent FT	100 percent FT*	100 percent FT*	100 percent FT*

Adhesion to Mead Carrier-Kote high wet strength paperboard (average of two bonds); *Recycled Clay Coated Boardstock (front/back), 40°F (4.4°C) rather than 30°F (-1°C); ** Substantially linear ethylene/1-octene interpolymers available from The Dow Chemical Company

Table Eighteen C: Packaging Adhesives

Reference #	Ex. 100	Ex. 101	Ex. 102	Ex. 103	Ex. 104
0.870 g/cm ³ I ₂ = 500 g/10 min**	37.3	29.9	39.9		
0.873 g/cm ³ ; I ₂ = 2200 g/10 min**				35	35
Affinity™ EG-8200				5	5
0.890 g/cm ³ ; I ₂ = 500 g/10 min**		7.5			
Sylvatac 1103					10
Eastotac H-130-R	29.9	29.9	29.9		
Eastotac H-100-R				25	29.7
Bareco PX-100			29.9		
Parafilm H4	32.4	32.4		29.7	
Paraffin 155				5	20
Irganox 1010	0.3	0.3	0.3	0.3	0.3
Visc. @350°F (177°C)	793 cps	810 cps	961 cps	1056 cps	1386 cps
100g Peel (°F(°C))	131 (55.0)	130 (54.4)	138 (58.9)	119 (48.3)	108 (42.2)
500g Shear (°F(°C))	198 (92.2)	203 (95.0)	200 (93.3)	199 (92.8)	146 (63.3)
Open T. (°C)				191	138
Set temp (°C)				124	117
Cloud Pt.				205	140
Bonding Test:					
-40°F (-40°C)	87 percent FT	50 percent FT	78 percent FT	68 percent FT	84 percent FT
0°F (-17°C)	81 percent FT	53 percent FT	80 percent FT	67 percent FT	67 percent FT
40°F (4.4°C)	88 percent FT	73 percent FT	88 percent FT	93 percent FT	92 percent FT
70°F (21°C)	100 percent FT	91 percent FT	98 percent FT	95 percent FT	87 percent FT
102°F (38.9°C)	99 percent FT	96 percent FT	99 percent FT	100 percent FT	100 percent FT

Adhesion to hard to bond corrugated, conditioned for 48 hours

Blends of Homogeneous Ethylene/ α -olefin Interpolymers and Oil:

Homogeneous ethylene/ α -olefin interpolymers are compatible with large quantities of oil, particularly when the interpolymer has a density of less than 0.880 g/cm³ and a melt index (I₂) of 30 g/10 min. or less. The following Tables Nineteen A-5 E set forth various blends of homogeneous ethylene/ α -olefin interpolymers and oil, and representative performance attributes thereof:

Table Nineteen A: Blends of Oil with a Substantially Linear Ethylene/1-Octene Interpolymer Having a Density of 0.902 g/cm³ and an I₂ of 30 g/10 min

10

Ingredient	33-3 Ex. 105	33-4 Ex. 106	33-5 Ex. 107	33-9 Ex. 108	33-10 Ex. 109	33-11 Ex. 110
Affinity™SM-1300	25	20	17.5	30	35	40
Kaydol Oil	70	70	70	70	70	70
Wt-percent Oil	73.7	77.7	80	70	66.7	63.6
Oil Exudation?	yes	yes	yes	yes	yes	yes

Table Nineteen B: Blends of Oil with a Substantially Linear Ethylene/1-Octene Interpolymer Having a Density of 0.870 g/cm³ and an I₂ of 30 g/10 min.

15

Ingredient	33-12 Ex. 111	33-13 Ex. 112	33-14* Ex. 113	33-15 Ex. 114
Affinity™ SM-8400	25	30	35	40
Kaydol Oil	70	70	70	70
Wt-percent Oil	73.7	70.0	66.7	63.6
Oil Exudation?	yes	yes	no	no

Table Nineteen C: Blends of Oil with a Substantially Linear Ethylene/1-Octene Interpolymer Having a Density of 0.868 g/cm³ and an I₂ of 0.5 g/10 min.

20

Ingredient	22-1 Ex. 115	22-2 Ex. 116	22-3* Ex. 117	22-4 Ex. 118
Affinity™ EG-8150	7	10	15	20
Kaydol Oil	70	70	70	70
Wt-percent Oil	90.9	87.5	82.3	77.8
Oil Exudation?	yes	yes	no	no

* Denotes lowest amount of polymer to achieve a non-exuding blend

Table Nineteen D: Blends of Oil with a Homogeneous Linear Ethylene/1-Butene Interpolymer Having a Density of 0.865 g/cm³ and an I₂ of 10 g/10 min.

Reference # Ingredient Trade Name	51-1 Ex. 119	51-2 Ex. 120	51-3 Ex. 121	41-1b* Ex. 122	41-2b Ex. 123	41-3b Ex. 124
SLP-0592	15	20	25	30	35	40
Kaydol Oil	70	70	70	70	70	70
Wt-percent Oil	82.3	77.8	73.7	70.0	66.7	63.6
Oil Exudation?	yes	yes	yes	no	no	no

5 **Table Nineteen E: Blends of Oil with a Homogeneous Linear Ethylene/Propylene Interpolymer Having a Density of 0.865 g/cm³ and an I₂ of 5 g/10 min.**

Reference # Ingredient Trade Name	51-4 Ex. 125	51-5 Ex. 126	51-6 Ex. 127	41-4b* Ex. 128	41-5b Ex. 129	41-6b Ex. 130
SLP-0394	15	20	25	30	35	40
Kaydol Oil	70	70	70	70	70	70
Wt-percent Oil	82.3	77.8	73.7	70.0	66.7	63.6
Oil Exudation?	yes	yes	yes	no	no	no

* Denotes lowest amount of polymer to achieve a non-exuding blend

10 Examples 105-130 of Tables Nineteen A-E demonstrate the tremendous oil holding power of homogeneous ethylene/ α -olefin interpolymers, particularly for homogeneous ethylene/ α -olefin interpolymers having a density of less than 0.880 g/cm³ and a melt index (I₂) of 30 g/10 min. or less. These oil rich blends exhibit a gel-like character and would be useful for skin attachment adhesives, particularly when combined with both solid and/or

15 liquid tackifying resins. Skin attachment adhesive may be applied to an article by means of slot coating, screen printing and spraying. Foaming of the adhesive to alter the compliance and adhesion properties is also contemplated. These gelatinous compositions are also surmised to have great utility in a variety of non-adhesive applications.

20 **Adhesives Comprising Homogeneous Ethylene/ α -Olefin Interpolymers and Polyamides**

The adhesives of the invention may further comprise one or more polyamides. Representative hot melt adhesives comprising a homogeneous ethylene/ α -olefin interpolymer and a polyamide, as well as representative performance attributes thereof, are set forth in the following Tables Twenty A and B.

Examples 131-143 yielded transparent, single phase adhesive compositions demonstrating the compatibility of the homogeneous ethylene/ α -olefin interpolymer with polyamides. All formulations yielded moderately high tack levels initially. Examples 133, 134, 135 and 136 were found to maintain moderate tack levels even after 72 hours of heat history. It is unexpected that the high softening point polyamides do not detract from the pressure sensitivity. Accordingly, the polyamides can be added to boost the performance of PSAs by increasing the heat resistance, creep resistances, and/or plasticizer resistance.

Table Twenty A: Adhesives Comprising a Homogeneous Ethylene/α-Olefin Interpolymer/Polyamide Blends

Ingredient	13-1 Ex. 131	13-2 Ex. 132	13-3 Ex. 133	13-4 Ex. 134	14-1 Ex. 135	14-2 Ex. 136	26-1 Ex. 137	26-2 Ex. 138
Affinity™ EG-8200	25	30	25	25	30	30		
Affinity™ EG-8150							25	30
Kaydol Oil	30	35	30	30	35	35	30	35
Eastman H-130	55	45	45	45	35	35	30	20
Polyamide HL-6088			10		10		15	15
Polyamide HL-2660				10		10		
Irganox 1010	0.3	0.3	0.3	0.3	0.3	0.3	0.3	0.3
Viscosity @ 3500F (177°C) (cps)	13000	20050	18600	17100	32150	30200		
Gel	Not Tested	Tested	no	no	no	no	Not Tested	Tested
Skin	"	"	no	slight	no	slight	"	"
Color	"	"	amber	dark amber	amber	dark amber	"	"
Separation	"	"	no	no	no	no	"	"

Table Twenty B: Adhesives Comprising a Homogeneous Ethylene/α-Olefin Interpolymer/Polyamide Blends

Ingredient	38-1	44-1	44-2	44-3	44-4
Ex. 139	Ex. 140	Ex. 141	Ex. 142	Ex. 143	
EIP #4	35	25	20	15	22.5
Kaydol Oil	25	25	25	25	25
Eastotac H-100	40	40	40	40	37.5
Polyamide HL-2660 (H.B. Fuller)					
Viscosity @ 350°F (cps)	22500	9600	6400	3480	9000
Appearance (Molten)	clear	hazy	hazy	hazy	hazy
Finger Tack	high	high	high	high	high
Adhesion Initial (Resistance)	high	high	high	high	not tested
Adhesion Aged 24 hrs/140°F (60°C)(Resistance)	moderate	high	high	high	not tested
Separation	no	no	no	slight	no
Gel	no	no	no	gel	no
Char	no	moderate	moderate	moderate	moderate

Insulation Bonding

The adhesives of the present invention may find further utility in insulation bonding. The following Table Twenty-One sets forth representative examples of such formulations, and representative performance attributes thereof:

Table Twenty One: Hot Melt Adhesives for Insulation Bonding

	Ex. 144	Ex. 145
0.890 g/cm ³ ; I ₂ = 2200 g/10 min**	69.5	
0.890 g/cm ³ ; I ₂ = 200 g/10 min**		30.5
Eastotac H-130R	30.0	44.5
Escorez 5400		
Polybutene M _w 1300		10.0
Benzoflex 352		10.0
Irganox 1010	0.5	0.5
Visc. @ 350°F (177°C)	2680 cps	1975 cps
SAFT (°F (°C))	182 (83)	166 (74)
PAFT (°F (°C))	126 (52)	132 (56)
Open time	less than 20 sec.	Less than 30-45 sec.

10

** Homogeneous ethylene/1-octene interpolymers available from The Dow Chemical Company

The above examples have been provided for the purpose of exemplification, rather than limitation. One skilled in the art will appreciate that the hot melt adhesives of the invention may be readily adapted for various applications. Accordingly, the invention shall be determined in accordance with the scope of the following claims:

1. A hot melt adhesive comprising:
 - (a) from 5 to 95 weight percent of at least one interpolymer which is a homogeneous ethylene/ α -olefin interpolymer characterized as having a density from 0.850 to 0.885 g/cm³;
 - (b) from 0 to 95 weight percent of at least one tackifier;
 - (c) from 0 to about 90 weight percent of at least one plasticizer; and
 - (d) from 0 to 90 weight percent of at least one wax;

wherein the sum of components (b), (c), and (d) comprises 5 to 95 weight percent of said adhesive composition.

2. A hot melt adhesive comprising:
 - (a) from 5 to 95 weight percent of at least one interpolymer which is a homogeneous ethylene/ α -olefin interpolymer characterized as having a weight average molecular weight (M_w) of less than 20,000;
 - (b) from 0 to 95 weight percent of at least one tackifier;
 - (c) from 0 to about 90 weight percent of at least one plasticizer; and
 - (d) from 0 to 90 weight percent of at least one wax;

wherein the sum of components (b), (c), and (d) comprises 5 to 95 weight percent of said adhesive composition.

3. A hot melt adhesive composition comprising:
 - (a) a homogeneous interpolymer of ethylene and greater than 30 weight percent as determined by mass balance, based on the total weight of ethylene and comonomer, of an α -olefin comonomer having from 3 to 20 carbon atoms, which copolymer has a weight average molecular weight (M_w) of from 2000 to 100,000; and
 - (b) a tackifier.

4. A hot melt adhesive comprising:
 - (a) from 30 to 97 weight percent of at least one first polymer which is an interpolymers of ethylene and at one C₃-C₂₀ α -olefin, said at least one first polymer being characterized as having:
 - (i) a density of from 0.850 to 0.885 g/cm³,
 - (iii) a number average molecular weight as determined by gel permeation chromatography, of less than 20,000;
 - (b) from 3 to 70 weight percent of at least one second polymer which is an ethylene homopolymer or an interpolymers of ethylene with at least C₃-C₂₀ α -olefin, the at least one second polymer being characterized as having:
 - (i) a density of from 0.910 to 0.970 g/cm³,
 - (ii) a number average molecular weight as determined by gel permeation chromatography, of less than 6,000; and
 - (c) from 0 to 70 weight percent of one or more tackifiers.
5. The adhesive of any of the preceding claims, wherein said adhesive is characterized as having a storage modulus (G') at 25°C of less than 1×10^7 dynes/cm² (1 MPa) and a glass transition temperature ranging from -65 to 30°C.
6. The adhesive of Claim 5 wherein the glass transition temperature ranges from 0 to 30°C.
7. The adhesive of any of the preceding claims, wherein the at least one C₃-C₂₀ α -olefin is selected from the group consisting of propylene, isobutylene, 1-butene, 1-pentene, 1-hexene, 1-heptene, 4-methyl-1-pentene, and 1-octene.
8. The adhesive of any of the preceding claims, where the at least one interpolymers has a density of 0.870 g/cm³ or less.

9. The adhesive of any of the preceding claims, wherein the at least one interpolymer has a melt index which is from 0.05 to 30 g/10 min.
10. The adhesive of any of the preceding claims, wherein the one or more tackifiers are provided in an amount greater than 5 weight percent, and wherein the softening point of the tackifier ranges from being flowable at ambient temperature to about 130° C.
11. The adhesive of any of the preceding claims, wherein the one or more plasticizers are provided in an amount totaling less than 30 weight percent, and is
 - (a) a phthalate, natural oil, paraffinic oil, naphthenic oil, aromatic oil, or
 - (b) a cyclohexane dimethanol dibenzoate compound, or
 - (c) a mixture of (a) and (b).
12. The adhesive of any of the preceding claims, wherein the at least one homogeneous ethylene/ α -olefin interpolymer is characterized as having a compositional distribution breadth index (CDBI) of at least 50 percent.
13. The adhesive of any of the preceding claims, further comprising a second homogeneous ethylene/ α -olefin interpolymer wherein:
 - (a) the number average molecular weight of the first and second interpolymers differs by at least 5000 or
 - (b) wherein the melt index of the first interpolymer is less than 30 g/10 min. and the melt index of the second interpolymer is greater than 100 g/10 min. or
 - (c) wherein the first and second interpolymers differ in density by at least 0.005 g/cm³.
14. The adhesive of any of the preceding claims, further comprising a second homogeneous ethylene/ α -olefin interpolymer wherein the melt index of the first interpolymer is less than 100 g/10 min. and the melt index of the second interpolymer is greater than 500 g/10 min.
15. The adhesive of any of the preceding claims, wherein the adhesive further comprises a modifying or extending composition selected from the group consisting of wax, styrenic block copolymers, polyamides, interpolymers or ionomers of ethylene and mixtures thereof.

16. The adhesive of Claim 22, wherein the modifying or extending composition is selected from the group consisting of ethylene/acrylic acid, ethylene/methyl acrylate, ethylene/isobutyl acrylate, ethylene/n-butyl acrylate, ethylene/methyl methacrylate copolymers and mixtures thereof.
17. An article comprising a tape or a label comprising a backing layer coated with the adhesive composition of the preceding claims.
18. The adhesive of any of the preceding claims, which further comprises greater than 70 weight percent of the homogeneous ethylene/ α -olefin interpolymer and wherein the interpolymer is characterized as having a density of from 0.850 to 0.965 g/cm³.
19. The adhesive of claim 26 wherein the density of the interpolymer is less than 0.860 g/cm³ and the melt index (I_2) is less than 30 gm/10 min.
20. A nonwoven article comprising a body fluid impermeable barrier bonded by a hot melt adhesive composition of any of the preceding claims.
21. The nonwoven article of Claim 20, wherein the adhesive comprises a single homogeneous ethylene/ α -olefin interpolymer having a density ranging from 0.865 to 0.890 g/cm³ and a melt index (I_2) which is 30 g/10 min or less.
22. The nonwoven article of Claim 20 or 21, wherein:
 - (a) the one or more tackifiers are provided in an amount of from 20 to 60 weight percent and
 - (b) the one or more plasticizers are provided in an amount totaling less than 30 weight percent.
23. The nonwoven article of any of Claims 21-22, wherein the plasticizer is a cyclohexane dimethanol dibenzoate compound.
24. The nonwoven article of any of Claims 21-22, further comprising a second homogeneous ethylene/ α -olefin interpolymer, wherein the first interpolymer has a density of less than 0.875 gm/cm³ and the second has a density of 0.890 g/cm³ or greater and wherein the first and second interpolymers have a melt index of greater than 1000g/10 min.
25. The nonwoven article of Claim 24 wherein the adhesive is applied by spraying or extrusion coating.

26. A polymerization process for preparing the adhesive of any of the preceding Claims comprising:
- a. reacting by contacting ethylene and at least one C₃-C₂₀ α-olefins under solution polymerization conditions, in the presence of a constrained geometry catalyst composition, in at least one reactor, to produce a solution of a first polymer which is an interpolymer of ethylene and the at least one C₃-C₂₀ α-olefin, the at least one first polymer being characterized as having:
 - (i) a density of from 0.850 to 0.920 g/cm³,
 - (iii) a number average molecular weight as determined by gel permeation chromatography, of from 5,000 to 80,000; and
 - (iv) a molecular weight distribution (M_w/M_n) of from 1.5 to 2.5;
 - b. reacting by contacting ethylene and, optionally, at least one second C₃-C₂₀ α-olefin, under solution polymerization conditions, in the presence of a constrained geometry catalyst composition or a heterogeneous catalyst composition, in at least one other reactor, to produce a solution of at least one second polymer, which is an ethylene homopolymer or an interpolymer of ethylene with the at least one second C₃-C₂₀ α-olefin, the at least one second polymer being characterized as having:
 - (i) a density of from 0.910 to 0.970 g/cm³,
 - (ii) a number average molecular weight as determined by gel permeation chromatography, of less than 6,000, and
 - (iii) a molecular weight distribution (M_w/M_n) of from 1.5 to 2.5;
 - c. combining the solution of the first reactor with the solution of the second reactor to form a solution of a blend;
 - d. removing the solvent from the solution of a blend of step (c) and recovering the blend; and

- e. optionally introducing a tackifier into the reactor of step (a), the reactor of step (b), or at any point subsequent to the reacting of step (b).
27. A case, carton or tray bonded with the hot melt adhesive of any of claims 1-19.
28. The case, carton or tray of claim 27 wherein the least one homogeneous ethylene/ α -olefin interpolymer of the adhesive composition has a melt index of 500 g/10 min. or less.
29. A book comprising a multiplicity of separate sheets stacked to form a book block adhered along one edge by a film of the adhesive of any of claims 1-19.

INTERNATIONAL SEARCH REPORT

International Application No
PC1/US 97/04161

A. CLASSIFICATION OF SUBJECT MATTER IPC 6 C08F2/00 C09J123/16		
According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED Minimum documentation searched (classification system followed by classification symbols) IPC 6 C08F C09J		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
Electronic data base consulted during the international search (name of data base and, where practical, search terms used)		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 115 434 A (EXXON RESEARCH ENGINEERING CO) 8 August 1984 see examples 1,3 ---	1,2,7,8
X	US 3 253 059 A (W.K.VOLLMER) 24 May 1966 see column 2, line 12 - line 21 ---	1
X	EP 0 608 175 A (NOVACEL SA) 27 July 1994 see page 3, line 17 - line 57 see page 4, line 15 - line 25; examples 2,3 ---	3
A	WO 94 10256 A (EXXON CHEMICAL PATENTS INC) 11 May 1994 see page 7, line 1 - page 15, line 8 --- -/--	1-29
<input checked="" type="checkbox"/> Further documents are listed in the continuation of box C. <input checked="" type="checkbox"/> Patent family members are listed in annex.		
* Special categories of cited documents :		
"A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier document but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. "&" document member of the same patent family	
Date of the actual completion of the international search <p style="text-align: center; font-weight: bold;">3 July 1997</p>	Date of mailing of the international search report <p style="text-align: center; font-weight: bold;">- 4. 08. 97</p>	
Name and mailing address of the ISA European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+ 31-70) 340-3016	Authorized officer <p style="text-align: center; font-weight: bold;">Schmidt, H</p>	

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 97/04161

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 92 12212 A (EXXON CHEMICAL PATENTS INC) 23 July 1992 see page 4, line 6 - page 11, line 13 ----	1-29
A	EP 0 442 045 A (HUELS CHEMISCHE WERKE AG) 21 August 1991 see page 3, line 3 - line 21; example 4 see page 2, line 54 - page 3, line 2 -----	1-29

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No
PCT/US 97/04161

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0115434 A	08-08-84	JP 59140277 A	11-08-84
US 3253059 A	24-05-66	NONE	
EP 0608175 A	27-07-94	FR 2700551 A	22-07-94
WO 9410256 A	11-05-94	CA 2148353 A	11-05-94
		DE 69306972 D	06-02-97
		DE 69306972 T	07-05-97
		EP 0666890 A	16-08-95
		ES 2096346 T	01-03-97
		JP 8503722 T	23-04-96
		US 5548014 A	20-08-96
WO 9212212 A	23-07-92	CA 2097303 A	28-06-92
		DE 69117534 D	04-04-96
		DE 69117534 T	14-08-96
		EP 0564596 A	13-10-93
		ES 2084346 T	01-05-96
		JP 6504082 T	12-05-94
EP 0442045 A	21-08-91	DE 4000696 A	18-07-91
		DE 59003015 D	11-11-93
		ES 2044375 T	01-01-94